

# SKAPS SW315

WOVEN GEOTEXTILE



## SKAPS INDUSTRIES

335 Athena Drive,  
Athens, GA 30601  
Ph: (706)-354-3700  
Fax: (706)-354-3737  
Email: contact@skaps.com

SKAPS woven geotextile fabrics are woven polypropylene materials offering optimum performance when used in stabilization applications. Produced from first quality raw materials, they provide the perfect balance of strength and separation in styles capable of functioning exceptionally well in a wide range of performance requirements.

Unless indicated below, all listed properties are Minimum Average Roll Values:

PROPERTY	TEST METHOD	ENGLISH (MARV <sup>2</sup> )	METRIC (MARV <sup>2</sup> )
Weight (Typical)	ASTM D 5261	6 oz/y <sup>2</sup>	204 g/m <sup>2</sup>
Grab Tensile	ASTM D 4632	315 lbs	1.40 kN
Grab Elongation	ASTM D 4632	15%	15%
Trapezoidal Tear	ASTM D 4533	120 lbs	0.533 kN
CBR Puncture Resistance	ASTM D 6241	1000 lbs	4.45 kN
Water Flow <sup>3</sup>	ASTM D 4491	4 gpm/sf	163 l/min/m <sup>2</sup>
Permittivity <sup>3</sup>	ASTM D 4491	0.05 Sec <sup>-1</sup>	0.05 Sec <sup>-1</sup>
AOS <sup>3</sup>	ASTM D 4751	40 US Sieve	0.425 mm
UV Resistance	ASTM D 4355	70/500 %/hrs	70/500 %/hrs

### PACKAGING

Roll Dimensions (W x L)	12.5 ft x 360 ft 17.5 ft x 258 ft	3.81 m x 110 m 5.33 m x 79 m
Area Per Roll	500 yd <sup>2</sup>	420 m <sup>2</sup>
Estimated Roll Weight	205 lbs	93 kg

### NOTES:

1. The property values listed above are subject to change without notice.
2. Minimum Average Roll Values (MARV) is calculated as the average minus two standard deviations. Statistically, it yields approximately 97.5% degree of confidence that any samples taken from quality assurance testing will meet or exceed the values described above.
3. At time of manufacturing. Handling may change these properties.

*This information is provided for reference purposes only and is not intended as a warranty or guarantee. SKAPS assumes no liability in connection with the use of this information.*