




Chemical Composition:	CaO	:	45-55%
	Al ₂ O ₃	:	35-45%
	SiO ₂	:	2.5-5%
	Fe ₂ O ₃	:	0.6-1.8%

DESMET

Size : 10 – 40 mm

Melting Point : 1250 - 1350°C

Bulk Density : 1100 - 1500 Kg/m³

Packing : HDPE Bags 25 – 50 Kg each.

Application : To use on ladle in secondary metallurgy.