

INTODUCTION

Kent Gaskets Grade
KG - E is a general
purpose commercial
Non asbestos. Mostly
recommended for
industrial water supply
and sewage in
parameters shown
below. The sheet is
manufactured in hot
alandering vulcanization
process in accordance
to high quality ISO 9001
standard procedures.

DATA SHEET

Commercial Grade Non Asbestos KG- E

MAXIMUM WORKING CONDITIONS		
PEAK TEMPERATURE	220 °C	
TEMPERATURE UNDER CONTINOUS OPERATION	150°C	
TEMPERATURE UNDER CONTINOUS OPERATION WITH STEAM	130 °C	
MAX. PRESSURE UNDER CONTINOUS OPERATION	MPa (bar) psi	4 (40 bar) 580 psi

PHYSICAL AND CHEMICAL PROPERTIES			
DENSITY +/- 5%	g/cm3	1,9	DIN28090-2
TRANSVERSE TENSILE STRENGTH MIN	MPa	4,0	DIN 52910
COMPRESSIBILITY, (TYPICAL VALUE)	%	6-16	ASTM F36
ELASTIC RECOVERY – MIN. 63280	%	50,0	ASTM F36
RESIDUAL STRESS 50MPa/16h/300°C	MPa	20,0	DIN 52913







CERTIFICATE NO. 19809 ISO9001

INCREASE IN THICKNESS			
MODEL OIL NO. 3 150°C/5h (MAX)	%	6	ASTM F146
MODEL FUEL B 20°C/5h (MAX)	%	9	ASTM F146
DISTILLED WATER 100°C/4h MAX	%	5	ASTM F146

The information given is based upon average values and is in no way intended as a warranty. The purchaser shall be responsible for determining the suitability of the product for any particular application.