



INTRODUCTION

Kent Gaskets Grade KG - Y has specially selected constituents and structure to ensure high tightness of a joint and resistance to a whole range of media, including steam, water, fuels, oils, solutions of salt as well as weak solutions of acids and bases. Thanks to application of a special composition of fibres and fillers, gaskets made of this material are very good in whole applications. This material is WRAS Approved suitable for potable water.



Kent Gaskets Ltd



@gaskets247



CERTIFICATE NO.19809
ISO9001

DATA SHEET

Non Asbestos BS7531 Grade Y KG- Y

MAXIMUM WORKING CONDITIONS		
PEAK TEMPERATURE	320 °C	
TEMPERATURE UNDER CONTINUOUS OPERATION	280°C	
TEMPERATURE UNDER CONTINUOUS OPERATION WITH STEAM	220 °C	
MAX. PRESSURE UNDER CONTINUOUS OPERATION	MPa (bar) psi	12 (100 bar) 1450

PHYSICAL AND CHEMICAL PROPERTIES			
DENSITY +/- 5%	g/cm3	1,9	DIN28090-2
TRANSVERSE TENSILE STRENGTH MIN	MPa	8,0	DIN 52910
COMPRESSIBILITY, (TYPICAL VALUE)	%	6-14	ASTM F36
ELASTIC RECOVERY – MIN. 63280	%	50	ASTM F36
MATERIAL GRADE REG. CLASSIFICATION BS 7531, RESIDUAL STRESS (16H/300°C) THK= 1,5 MIN	MPa	23,4 Grade Y	BS 7531

INCREASE IN THICKNESS			
OIL IRM 903 150°C/5h (MAX)	%	5	ASTM F146
MODEL FUEL B 20°C/5h (MAX)	%	7	ASTM F146
DISTILLED WATER 100°C/4h MAX	%	2	ASTM F146

The information given is based upon average values and is in no way intended as a warranty. The purchaser shall be responsible for determining the suitability of the product for any particular application.