

PETRONAS GREASE LiX EP 2/170

Extreme Pressure Lithium Complex Grease with Approvals from OEM Commercial Vehicle

PETRONAS Grease LiX EP 2/170 is an extreme pressure Lithium complex grease specifically developed for commercial vehicle applications and a wide variety of industry applications. Formulated with selected mineral base oil enhanced with Lithium Complex soap, advanced extreme pressure, anti-oxidant, anti-rust and corrosion inhibitor additives, PETRONAS Grease LiX EP 2/170 provides excellent load carrying capabilities and wear protection, high resistance to water wash-out and rust inhibition, even at elevated temperatures.

PETRONAS Grease LiX EP 2/170 meet or exceeds key industrial specifications and OEM requirements.

Applications

PETRONAS Grease LiX EP 2/170 is recommended for use in:

- general purpose applications for automotive commercial transport vehicles and chassis lubrication. It is particularly suitable for lubricating of roller and friction bearings under extreme pressure load at high temperature
- wheel bearing and prop shaft lubrication of commercial / utility vehicles and passenger motor cars
- industrial and farm equipment components

Note: PETRONAS Grease LiX EP 2/170 is recommended for operating temperature range of -25°C to +140°C.

PETRONAS GREASE LiX EP 2/170

Extreme Pressure Lithium Complex Grease with Approvals from OEM Commercial Vehicle

Features and Benefits

Features	Benefits
High pumpability	High performance where low temperature performance is required
Excellent adhesive and cohesive properties	Excellent grease tenacity which helps reduce leakage and extend re-lubrication intervals, reducing maintenance costs
Excellent load carrying capacity	Contains special additives which enables the grease to withstand heavy loads without loss of the lubricant film
High rust & corrosion protection	Protects bearing surfaces against rust and corrosion, even when the grease is contaminated with water
High resistance to water wash-out	Equipment protection and good lubrication even in presence of water
High thermal and oxidation stability	Has good oxidation resistance and can withstand high operating temperatures without hardening or forming bearing deposits
Mechanical stability	A highly stable grease with little or no change to consistency when worked in the lubrication of bearings

PETRONAS GREASE LiX EP 2/170

Extreme Pressure Lithium Complex Grease with Approvals from OEM Commercial Vehicle

Typical Properties

Characteristic	Method	Specification	LiX EP 2/170
Thickener Type	-	Lithium Complex	Lithium Complex
NLGI	ASTM D217	2	2
Color	Visual	Green	Green
Worked Penetration, mm/10	ASTM D217	265 – 295	280
Worked Penetration 100.000x, Penetration Change, mm/10, Max.	ASTM D217	+20	+15
Oil Separation, Mass %, Max.	ASTM D1742	5	3
Dropping Point, °C, Min.	ASTM D2265	260	265
Four Ball Wear, mm, Max.	ASTM D2266	0.50	0.40
Four Ball EP Weld Point, Min.	ASTM D2596	250	250
Roll Stability, % of Penetration Change, Max.	ASTM D1831	15	10
Wheel Bearing Leakage, grams, Max.	ASTM D4290	8	5
Water Washout, %, Max.	ASTM D1264	8	6
Rust Protection, rating	ASTM D1743	Pass	Pass
Water Resistance	DIN 51807/1	0-90	0-90
Copper Corrosion, Max.	ASTM D4048	1	1a
Emcor Test (Distilled Water), rating	ASTM D6138	0-0	0-0
Base Oil Viscosity @40°C, cSt	ASTM D445	160 - 180	170

All technical data is provided for reference only and all specification based on ASTM D4950 / SS is available upon request including quality control limits

Performance Levels

- DIN 51502 KP2N-25
- GC-LB
- ISO 12924 XBDIB2
- MAN 284 Li-H2
- MB 265.1
- VOLVO Std 1277.2 (97720)

PETRONAS GREASE LiX EP 2/170

Extreme Pressure Lithium Complex Grease with Approvals from OEM Commercial Vehicle

Health, Safety and Environment

This product is unlikely to present any significant health and safety hazards when used in the recommended application. Avoid contact with skin. Wash immediately with soap and water after skin contact. Do not discharge into drains, soil or water.

For further detail regarding storage, safe handling, and disposal of product, please refer to product SDS or contact us at: www.pli-petronas.com

Important Note

The word PETRONAS, the PETRONAS logo and such other related trademarks and/or marks used herein are trademarks or registered trademarks of PETRONAS Lubricants International Sdn. Bhd. ("PLISB"), or its subsidiaries or related Holding Corporation under license unless indicated otherwise. The PLI Documents and the information contained herein is believed to be accurate as of the date of printing. PLISB makes no express or implied representation or warranties as to its accuracy or completeness or information in or any transaction performed. The PLI Documents information provided is based on standard tests under laboratory conditions and is given only as a guide. Users are advised to ensure that they refer to the latest version of these PLI Documents. It is the responsibility of the users to evaluate and use products safely, to assess suitability for the intended application and to comply with all applicable laws and regulations imposed by the respective local authorities.

Safety Data Sheets are available for all our products and should be only be consulted for appropriate information regarding storage, safe handling and disposal of the product. No responsibility shall be taken by either PLISB or its subsidiaries and related holding corporation for any loss or injury or any direct, indirect, special, exemplary, consequential damages or any damages whatsoever, whether in action of contract, negligence or other tortious action, in connection or resulting from abnormal use of the materials and/or information, from any failure to adhere to recommendations, or from hazards inherent in the nature of the materials and/or information. All products, services and information supplied are under our standard conditions of sale. Please consult with any of our local representative in the event you require any further information.