

# Changzhou Senhong Decorative Materials Co., LTD.

# **TEST REPORT**

### **SCOPE OF WORK**

AQUA FLOOR (Laminate Floor)

# **REPORT NUMBER**

200424005SHF-011

# **TEST DATE(S)**

2020-04-24 - 2020-05-27

# **ISSUE DATE**


2020-05-27

### **PAGES**

5

### **DOCUMENT CONTROL NUMBER**

LFT-APAC-SHF-OP-10k(May 1, 2020) © 2020 INTERTEK



Intertek Testing Services Shenzhen Ltd. Shanghai Fengxian Branch





Intertek Testing Services Shenzhen Ltd. Shanghai Fengxian Branch
Plant 5, No. 6958 Daye Road, Fengxian District, Shanghai, China
Tel: 021-61136116 Fax: 021-61189921

Website: www.intertek.com

# **Test Report**

# **Statement**

- 1. This report is invalid without company's special seal for testing on assigned page.
- 2. This report is invalid without authorized person's signature.
- 3. This report is invalid where any unauthorized modification indicated.
- 4.Don't copy this report in partial (except full copy) without any official approval in written by our company. This report is invalid without re-stamping the special seal for testing in copying report.

5.Any holder of this document is advised that this report is for the exclusive use of Intertek's Customer and is provided pursuant to the agreement between Intertek and its Customer. Intertek's responsibility and liability are limited to the terms and conditions of the agreement. This report was made with due care within the limitation of a defined scope of work and on the basis of information, materials and instructions received from the Customer or its nominated third parties. Intertek is under no obligation to refer to or report upon any facts or circumstances which are outside the specific instructions received and accepts no responsibility to any parties whatsoever, following the issue of the report, for any matters arising outside the agreed scope of the works. The tests results are not intended to be a recommendation for any particular course of action. Customer is responsible for acting as it sees fit on the basis of such results.

6.Intertek's written consent is required to use Intertek's name or logo on the object, product or service being tested. The observations and test results in this report relate only to the sample under test. This report alone does not indicate that the item, product or service has passed any Intertek certification program.

7. The report was digital signed by Shang Hai, Intertek Group plc, please using Adobe Acrobat Reader to verify the authenticity.





Intertek Testing Services Shenzhen Ltd. Shanghai Fengxian Branch Plant 5, No. 6958 Daye Road, Fengxian District, Shanghai, China

Tel: 021-61136116 Fax: 021-61189921 Website: www.intertek.com

# **Test Report**

Issue Date: 2020-05-27 Intertek Report No. 200424005SHF-011

Applicant: Changzhou Senhong Decorative Materials Co., LTD.

Address: Qinxin Village, Yaoguan Town, Wujin District, Changzhou, Jiangsu, China

Attn: Tonny

Test Type: Performance test, samples provided by the applicant.

### **Product Information**

<b>Product Name</b>	AQL	A FLOOR (Laminate Floor	Brand	/	
Sample		Good Condition		Sample Amount	100 pcs
Description				Received Date	2020-04-24
Sample ID		Model		Specification	
S200424005SHF.009		/		1215x145mmx12mm	

### **Test Methods And Standards**

Test Standard	ASTM D6007-14
Specification Standard	/
Test Conclusion	The samples were tested according to the above standards, and the results are shown in the following page.

# Note:

1. This report relates specifically to the sample(s) that were drawn and provided by the applicant or their nominated third party. The reported result(s) provide no warranty or verification on the sample(s) representing any specific goods and/or shipment and only relate to the sample(s) as received and tested.

**Report Authorized** 

Name! Flora Fan

Title: Reviewer Title: Project Engineer

Name:

Version: 1 May 2020 Page 3 of 5 LFT-APAC-SHF-OP-10k

Tod Qian

*Qian* 



# **Test Report**

Issue Date: 2020-05-27 Intertek Report No. 200424005SHF-011

# Test Items, Method and Results:

Test Item: Formaldehyde content test

Test Method: As per ASTM D6007-14 small scale chamber method, formaldehyde content was detected by UV-VIS spectrophotometer.

Test condition:

Chamber type: 0.225 m<sup>3</sup> stainless steel chamber

Climatic conditions: 25°C, 50% R.H.

Air exchange rate:  $0.5 \text{ h}^{-1}$ Loading factor:  $0.43 \text{ m}^2/\text{m}^3$ Test result: 0.06 ppm

Note:

1. ppm = parts of formaldehyde per million parts air

2. Detection limit = 0.02 ppm

3. The sample was conditioned at 24±3 °C, 50±5% relative humidity for seven days before the testing.

4. Test location: Central Chemical Lab of Intertek Testing Services Ltd., Shanghai Address: Block B, Jinling Business Square, No. 801, Yi Shan Road, Shanghai, China





# **Test Report**

Issue Date: 2020-05-27 Intertek Report No. 200424005SHF-011

# **Appendix A: Sample Received Photo**



Front View(Test Surface)

Back View

# **Revision:**

NO.	Date	Changes	Author	Reviewer
200424005SHF-011	2020-05-27	First issue	Tod Qian	Flora Fan

