

PolyDissolve™ S1

PolyDissolve™ S1 is a water dissolvable support for PLA, TPU, PVB and Nylon based filaments from our portfolio. It is specifically engineered to have a perfect interface with these materials while also displaying good solubility.

Physical Properties

Property	Testing method	Typical value
Density	ASTM D792 (ISO 1183, GB/T 1033)	1.37 (g/cm ³ at 21.5 °C)
Melt index	220 °C, 2.16 kg	7.8 (g/10 min)

Tested with 3D printed specimen of 100% infill

Material Compatibility

Material	Adhesion with PolySupport™
PLA based material from Polymaker's portfolio	++
PETG based material from Polymaker's portfolio	+
ABS based material from Polymaker's portfolio	--
PC based material from Polymaker's portfolio	--
PVB based material from Polymaker's portfolio	++
TPU based material from Polymaker's portfolio	++
Nylon based material from Polymaker's portfolio	++

++ support the model very well

+ generally support the model depending on its geometry

- generally doesn't support the model depending on its geometry

-- do not support the model

Recommended printing conditions

Parameter	
Nozzle temperature	215 - 225 (°C)
Build Surface material	BuildTak®, Blue Tape
Build surface treatment	None
Build plate temperature	25 - 60 (°C)
Cooling fan	Turned on
Printing speed	30-40 (mm/s)
Raft separation distance	0 (mm)
Retraction distance	1 (mm)
Retraction speed	20 (mm/s)
Recommended environmental temperature	Room temperature

Based on 0.4 mm nozzle and Simplify 3D v.3.1. Printing conditions may vary with different nozzle diameters

It is highly recommended to use the PolyBox™ when printing with PolyDissolve™ S1 and to store it in the resealable bag.

Disclaimer:

The typical values presented in this data sheet are intended for reference and comparison purposes only. They should not be used for design specifications or quality control purposes. Actual values may vary significantly with printing conditions. End- use performance of printed parts depends not only on materials, but also on part design, environmental conditions, printing conditions, etc. Product specifications are subject to change without notice.

Each user is responsible for determining the safety, lawfulness, technical suitability, and disposal/recycling practices of Polymaker materials for the intended application. Polymaker makes no warranty of any kind, unless announced separately, to the fitness for any use or application. Polymaker shall not be made liable for any damage, injury or loss induced from the use of Polymaker materials in any application.