



# **Weld Schedule Guide**

#### Electrode Diameter And Shape Material Welding Current Weld Time Weld Minimum Tension-Minimun Weld Minimum Net Contacting Thicknes Electrod Nugget Size (Approx. Spacing Force Shear Strengt notes 1, 2 & 3 note 4 D d Oc Inches In. In Deg Lb Amps. ycles In. Lb. Inches Inches 0.022 550 5/8 3/16 120 300 13000 8 0.15 5/8 5/8 0.030 5/8 3/16 120 400 13000 10 0.16 1000 5/8 5/8 0.036 5/8 1/4 120 500 13500 12 0.19 1180 3/4 5/8 0.039 5/8 1/4 120 650 14000 13 0.21 1400 3/4 5/8 0.052 5/8 1/4 120 725 14500 18 0.22 1700 7/8 11/16 0.063 3/4 1/4 120 850 15500 22 0.24 2500 1-1/8 3/4 24 0.078 3/4 1200 19000 3200 7/8 120 0.28 1-1/4 5/1 0.093 3/4 3/8 120 1400 21000 30 0.34 4200 1 - 1/21 0.108 7/8 3/8 120 1750 20000 37 0.40 5900 1-3/4 1 - 1/80.123 7/8 3/8 120 2000 20000 42 0.48 7200 2 1-1/8

Spot welding galvanized low-carbon steel

### Projection welding galvanized low-carbon steel

Material Thickness	Diar	trode neter Shape	Net Electrode Force	Welding Current (Approx.)	Weld Time	Weld Nugget Size	Minimum Tension- Shear Strength	Projec Siz	
notes 1, 2, & 3	note 4						(For Single Projections Only)		
	F						Ully)	L	
	-d-t								
	D	d						Diameter	Llaight
Inches	ln.	ln.	Lb.	Amps.	Cycles	ln.	Lb.	In.	Height In.
0.039	5/8	3/8	250	10000	15	0.15	925	0.187	0.041
0.063	5/8	7/16	400	11500	20	0.25	2050	0.218	0.048
0.078	3/4	1/2	550	16000	25	0.25	2700	0.250	0.054
0.093	3/4	1/2	750	16000	30	0.30	4300	0.250	0.054
0.108	7/8	1/2	950	22000	33	0.31	4900	0.250	0.054

#### NOTES:

1. Material must be free from dirt, grease, paint etc. prior to welding, but may have light oil.

2. Two equal metal thicknesses of each gage.

3. Commercial coating weight is 1.25 oz. per square foot.

4. Electrode Material-RWMA Group A, Class 2.

5. Water Cooling: 2 gallons per minute.

Projections should be larger in diameter for galvanized than for uncoated material.

Material Thickness	Electrode Width And Shape		Net Electrode Force	Welding Current (Approx.)	Weld Time		Welding Speed	Welds Per Inch	Minimum Contacting Overlap		
notes 1, 2, & 3	note 4								EXTERNA		
		Ű			Heat Time	Cool Time					
	۰ w	- E    E							States -		
	vv	E									
Inches	ln.	ln.	Lb.	Amps.	Cycles	Cycles	ln./Min.	W/ln.	Inches		
0.015	3/8	1/4	900	15000	2	2	120	7.5	3/8		
0.036	1/2	1/4	1100	18000	4	2	60	10.0	1/2		
0.039	1/2	1/4	1200	19000	4	3	60	9.0	1/2		
0.052	1/2	1/4	1350	20000	5	1	90	7.0	9/16		
0.063	1/2	5/16	1500	19800	8	2	54	7.0	5/8		
0.078	5/8	5/16	1850	23000	10	7	30	7.0	11/16		

## Seam welding galvanized low-carbon steel

#### NOTES:

- 1. Material must be free from dirt, grease, paint etc. prior to welding, but may have light oil.
- 2. Two equal metal thicknesses of each gage.
- 3. Commercial coating weight is 1.25 oz. per square foot.
- 4. Electrode Material-RWMA Group A, Class 2.
- 5. Pressure-tight joints require stripping the zinc coating prior to welding.
- 6. Nominal electrode diameter ranges between 8 to 10 inches.

From American Welding Society "Recommended Practices for Resistance Welding."

**COPYRIGHT NOTICE:** All reproductions of this document are the property of Tuffaloy Products, Inc. and may not be reproduced, published, changed or used in any way without prior written consent.