Architectural Specification -- Natural Quartz, Single Broadcast

100% Solids Epoxy - Silica Sand Single Broadcast Nominal 1/16" Flooring System

Part 1: General

1.01 System Description

- A. Squeegee & Roller-applied 100% solids, penetrating epoxy primer followed by a squeegee & roller-applied, 100% solids epoxy basecoat with a broadcast of 30-50 mesh silica sand and sealed with grout coat of 100% solids epoxy and a final top coat of aliphatic urethane, to achieve a nominal 1/16" (1.59 mm) thick, heavy-duty floor system.
- B. This system shall be applied to the prepared substrate(s) as defined by the plans strictly in accordance with the manufacturer's recommendations.

1.02 Submittals

A. Product Data

1. Current edition of manufacturer's product literature including physical data, chemical resistance, surface preparation, and application instructions.

B. Samples

1. A hard sample of the proposed system shall be submitted to represent the finished system.

C. Warranty

- 1. Manufacturer's standard warranty
- 2. Applicator's standard warranty

1.03 Quality Assurance

A. Qualifications

- 1. The manufacturer shall have a minimum of ten (7) years' experience in the production, sales, and technical support of polymer-based floor coatings.
- 2. The applicator shall have a minimum of three (3) years' documented experience in the application of polymer floor coatings to concrete floors.
- 3. Proposed suppliers shall provide certification that they have ten (7) years' experience in the production of polymer floor coatings and be required to meet all provisions of this specification as well as provide evidence for compatibility between components to the satisfaction of the Architect.

B. Pre-Bid Conference

1. A pre-bid conference should be held between prospective applicators and the Architect to review surface preparation, application, clean-up procedures, and design issues.

C. Packing and Shipping

1. All materials are to be delivered to the job site in the manufacturer's original packaging. The product code and other identification marks should be clearly marked and visible.

D. Storage and Protection

- 1. All material is to be stored in a cool, dry place out of the direct sunlight and away from any ignition sources. The applicator should refer to the manufacturer's literature and material safety data sheets for more information.
- 2. Material Safety Data Sheets are to be kept on site and made readily available for all personnel.
- 3. Keep containers sealed and ready for use.

1.04 Project Conditions

A. Environmental Requirements

- 1. Optimum air and substrate temperature for product application is between 70° F (21° C) and 85° F (29° C). For temperatures outside of this range, consult the manufacturer for product application suggestions.
- 2. Verify the work environment is properly equipped with vapor barriers and perimeter drains.
- 3. Maintain proper lighting throughout the work environment; it is important to have permanent lighting in place or a close equivalent before installation of floor system.
- 4. Store and dispose of any waste in accordance with regulations of local authorities.

B. Safety Requirements

- 1. "No Smoking" signs shall be posted throughout the work area prior to application.
- 2. The owner shall be responsible for removing any foodstuffs from the work area.
- 3. Open flames, spark producing tools/items, and ignition sources shall be removed from the work area prior to application.
- 4. Only work-related personnel shall be allowed within the work area.

1.05 Warranty

A. Coordination

The manufacturer offers a full, one-year warranty against defects in materials.
 Warranties concerning the installation of the material are solely the responsibility of the applicator.

Part 2: Products

2.01 Manufacturers

A. Petra Coatings LLC 134 County Road 2691 Alvord, TX 76225

Phone: (940) 872-8832 Fax: (940) 872-8833

http://www.PetraCoatings.com

2.02 Materials

A. Primer

1. The primer shall be a 100% reactive, epoxy-based, penetrating primer that exhibits chemical resistance: Petra Coatings WH7000 100% Solids Epoxy.

B. Basecoats

1. The basecoat shall consist of a tough, impact-resistant epoxy coating in thickness capable of accepting aggregate: Petra Coatings – WH7000 100% Solids Epoxy.

C. Broadcast

1. Broadcast 30-50 mesh silica sand (or 40s quartz aggregate) into the wet basecoat, at .33 pounds per square feet until no wet spots are visible (broadcast to refusal).

D. Grout Coat(s)

1. Grout with a two-component, 100% solids epoxy grout coat. Apply a second grout coat if no optional finish coats are to be applied: Petra Coatings – WH7000.

E. Optional Topcoat(s)

1. Apply 1 to 2 topcoat(s) of a Petra Coatings high performance, color-stable urethane, exhibiting excellent chemical and abrasion resistant properties: Petra Coatings – Aliphatic Urethane.

2.03 Properties

A. The coating system should meet the following physical properties:

Cured System Properties

Chemical Properties	Natural Quartz, Single Broadcast
Compressive Strength, ASTM C695	10,000 psi
Tensile Strength, ASTM D638	4,000 psi
Tensile Elongation ASTM D638	7.5%
Flexural Strength ASTM D790	6,250 psi
Bond Strength to Concrete ACI-403	335 PSI Concrete fails
Hardness, Shore D, ASTM D2240	75-80
Impact Resistance, MIL D-3134	No cracking or delamination

Coefficient of Linear Expansion ASTM D-696	12°F to 140°F
Abrasion Resistance Taber Abrader (CS-17 Wheels, 2000gm. Load, 1000 cycles)	Avg. 24.0 mg. loss
Water Absorption, ASTM D570	0.04%
Linear Shrinkage ASTM D-2566	0.02%
Electrical Conductivity	Non-conductive
Flammability, ASTM D635	Self-Extinguishing

Part 3: Execution

3.01 Inspection

A. General

 Examine the areas and conditions where Natural Quartz Single Broadcast is to be installed and notify the Architect of conditions detrimental to the proper and timely completion of the work. Do not proceed with the work until unsatisfactory conditions have been corrected by the contractor in a manner acceptable to the Architect.

3.02 Preparation

A. General

1. Consult the manufacturer's recommendations for concrete substrate preparation before proceeding.

B. Patching and Joint Preparation

 Before application, the floor shall be examined for spalls, pitting, holes, cracks, nonfunctional joints, etc. These must be treated after preparation and before application. Patch with Petra Coatings semi-rigid PCJ Filler. For functional or expansion joints, these shall be treated with elastomeric resin having a minimum elongation of 100%, Petra Coatings ElastoFill (caulk gun applied).

C. Concrete Surfaces

 Shot-blast, or diamond grind as required to obtain clean, open porous concrete. Remove sufficient material to provide a sound surface, free of laitance, glaze, efflorescence, and any bond-inhibiting curing compounds or form release agents. Remove grease, oil, and other penetrating contaminants. Repair damaged and deteriorated concrete to acceptable condition; leave surface free of dust, dirt, laitance, and efflorescence.

D. Materials

1. Mix components when required, and prepare materials according to flooring system manufacturer's instructions.

3.03 Application

A. General

- 1. The system shall be installed in the order described below:
 - a. Substrate Preparation

- b. Priming
- c. Basecoat and Broadcast Applications
- d. Grout Coat Applications
- e. Topcoat Applications
- Concrete surfaces on grade shall have been constructed with a vapor barrier to protect against the effects of vapor transmission and possible delamination of the system. Refer to manufacturer's concrete preparation instructions for additional recommendations.
- 3. The surface should be dry prior to application of any of the aforementioned steps. Furthermore, the substrate shall always be kept clean, dry, and free of any contaminants.
- 4. The handling and mixture of any material associated with the installation of the system shall be in accordance with the manufacturer's recommendations and approved by the Architect.
- 5. The system shall follow the contours of the substrate unless otherwise specified by the Architect.
- 6. A neat finish with well defined boundaries and straight edges shall be provided by the applicator.

B. Priming

- 1. All areas considered for the application shall be primed with the manufacturer's primer to seal and penetrate the substrate in preparation for applying the basecoat and grout coat.
- 2. Porous concrete substrates may require additional applications of primer.

C. Basecoat & Broadcast

- The basecoat shall consist of the manufacturer's approved epoxy resin with a broadcast of approved silica sand to resurface the floor, seal the surface, and give the floor impact and chemical resistance.
- 2. Slip-resistant properties are provided through the broadcast of silica sand into the basecoat application.

D. Grout Coat(s)

1. The grout coat(s) shall be consistent with the manufacturer's recommended epoxy grout coat for the system.

E. Optional Topcoat(s)

- 1. Optional topcoat(s) shall be consistent with the manufacturer's recommendation for the system.
- 2. No traffic or equipment shall be permitted on the floor during the curing period.

3.04 Field Quality Control

- A. Tests & Inspection
 - 1. The following tests shall be performed by the applicator and recorded during application to submit to the Architect:
 - a. Temperature during installation
 - 1. Air
 - 2. Substrate
 - 3. Dew Point
- 3.05 Cleaning
 - A. Disposal
 - 1. Properly remove and dispose of any excess materials.