

WALNUT MEDIUM (12-20)

PRODUCT DATA

Physical Properties

Tested Property	Typical
Appearance	Granular
Colour	Brown
Flash Point	193.3°C
Charring Temperature	243.3°C
Hardness (MOH)	3.5
Hardness (Rockwell)	91



Walnut Medium (12-20)

Chemical Properties

Tested Property	Typical
Nitrogen	0.10%
Cellulose	40-60%
Lignin	20-30%
Toluene Solubility	0.5-1.0%
Methoxyl	6.5%
Chlorine	0.10%
Ash	1.5%
Cutin	1.0%

Typical Particle Distribution

International (mm/µm)	American (inch/sieve)	Batch typical % Through Screen
2.36mm	8	100
1.70mm	12	96-97
1.40	14	5
850µm	20	0-1

Recommendations given in this bulletin are based on tests believed to be reliable. However, the use of the information is beyond the control of Integrity Chemical Solutions Inc. and no guarantee, expressed or implied is made to the results obtained if not used in accordance with directions or established safe practice. The buyer must assume all responsibility, including injury or damage from the misuse of the product as such, or in combination with other materials. This bulletin is not to be taken as a license to operate under or recommendation to infringe any patent.