


RSC156P(MCCE)- PID RESISTANT

5BB(C) POLY HALF CELL




FEATURES

- Ozonized PID resistant process
- Tighter color variation control^①
- <1.0mm graphite boat button size^②
- >1.5N peel strength for Front Ag busbar^③
- >2.0N peel strength for Back Ag busbar^③
- Cell bow <2.0mm

TEMPERATURE COEFFICIENTS^④

Voc (β)	-0.33% /°C
Isc (α)	+0.06% /°C
Pmp (γ)	-0.40% /°C

SPECTRAL RESPONSE, IQE AND IRRADIANCE DEPENDENCE^④



Irradiance W/m ²	Isc*	Voc*	Pmp*
1000	1.00	1.00	1.00
800	0.80	0.99	0.79
600	0.60	0.98	0.59
400	0.40	0.96	0.38
200	0.20	0.93	0.18

Values normalized to 1000 W/m² Irradiance

MECHANICAL DATA & DESIGN

Format	156.75mm × 156.75mm ± 0.25mm
Thickness	220 ± 20μ / 200 ± 20μ
Front	0.7mm wide continuous BB SiN Blue ARC
Back	1.8mm exposed BB width Al BSF

CELL SPECIFICATION

Eff, %	Pmpp, W	Vmpp, V	Imp, A	Voc, V	Isc, A	FF, %
19.30	4.74	0.545	8.72	0.640	9.22	80.55
19.20	4.72	0.544	8.69	0.639	9.20	80.46
19.10	4.69	0.542	8.67	0.637	9.17	80.44
19.00	4.67	0.541	8.64	0.636	9.15	80.43
18.90	4.64	0.540	8.62	0.635	9.12	80.41
18.80	4.62	0.539	8.60	0.634	9.10	80.35
18.70	4.59	0.537	8.57	0.633	9.08	80.21
18.60	4.57	0.536	8.55	0.632	9.05	80.15

Measurements at Standard Test Conditions (STC), 1000W/m², 25°C, AM1.5G Spectrum

- ① Ref: Our Optical Inspection Standard; Please contact sales@risunsolar.com for the document.
 - ② Graphite button mark not protruding the extreme fingers or cover fingers.
 - ③ Peel strength test referenced to 180° peel angle using Auto Tab Pull Tester.
 - ④ Temperature coefficients, Spectral response, IQE curve and Irradiance dependence measured at National Center of Supervision and Inspection on Solar PV products Quality, CPVT Testing lab, Wuxi, China.
- Remark:** Product specifications are subject to change without notice. Our reserves the right for the final interpretation of all figures reported in this specification document.