

Hempel's Polyenamel 55102

Product characteristics

Description

Hempel's Polyenamel 55102 is a two-component, high-gloss acrylic polyurethane enamel cured with aliphatic isocyanate, with good gloss and colour retention.

Complies with EU Directive 2004/42/EC, The Paints Directive on the limitation of volatile organic compounds: subcategory j.

Recommended use

As a glossy decorative topcoat in severely corrosive atmospheric environments on properly prepared metals such as aluminium, stainless steel and galvanized steel. Excellent adhesion on wood and glass-fibre reinforced polyester

Service temperature:

- Maximum, dry exposure only: 120°C [248°F].

Certificates / Approvals

- Complies with the European Fire Standard EN 13501-1, fire reaction class: B-s1, d0.

Product safety

Flash point 35°C [95°F]

VOC content mixed product

Legislation	Value	5% thinning, by volume	Limit value, phase II (2010) ^a
EU	440 g/L [3.67 lb/US gal]	461 g/L [3.85 lb/US gal]	500 g/L [4.17 lb/US gal]
US (coatings)	440 g/L [3.67 lb/US gal]	-	-
US (regulatory)	440 g/L [3.67 lb/US gal]	-	-
China	440 g/L [3.67 lb/US gal]	-	-

According to specific legislation, see details in the Explanatory Notes available at Hempel website, hempel.com or at your local Hempel website. VOC values may vary with shade, please consult the Safety Data Sheet, section 9. ^aEU Directive 2004/42/CE.

Handling

Handle with care. Before and during use, observe safety labels on packaging and paint containers and follow all local and national safety regulations. Always consult Hempel's Safety Data Sheet for this product along with the Product Data Sheet.

For professional use only.

Product data

Product code

55102

Product components

Base 55107
Curing agent 95304

Standard shade* / code

White 10000 **

Gloss

High-gloss

Volume solids

52 ± 2%

Specific gravity

1.2 kg/L [10 lb/US gal]

Reference dry film thickness

35 micron [1.4 mils]

Aluminium shade / code

Aluminium grey 19001 ***

Gloss

Please consult Hempel's Guideline on aluminium pigmented coatings.

Volume solids

45 ± 2%

* Wide range of colours is available via Hempel's Multi-Tint® system.

** Colour stability may be affected by exposure to harsh chemical and/or high temperatures.

*** Appearance of the aluminium pigmented coats will depend on application method, drying conditions, handling etc. Please see the Guideline on Aluminium pigmented coatings at hempel.com or at your local Hempel website.

Hempel's Polyenamell 55102

Specific gravity
1 kg/L [8 lb/US gal]

Reference dry film thickness
35 micron [1.4 mils]

Surface preparation

Cleanliness

- According to Hempel's Specification.

New build:

- According to Hempel's Specification.

Maintenance and Repair

- According to Hempel's Specification.

Consult Hempel's separate Surface Preparation Guidelines for more details.

Application

Mixing ratio

Base 55107 : Curing agent 95304
(4 : 1 by volume)

Stir well before use.

Thinner

Hempel's Thinner 08080
Hempel's Thinner 08880

Cleaner

Hempel's Thinner 08080
Hempel's Thinner 08510

Pot life

Product temperature	20°C [68°F]
----------------------------	-----------------------

Pot life	2 hours
----------	---------

Application method

Tool	Thinning max vol.	Application parameters
Airless spray	5%	Nozzle pressure: 75-100 bar [1100 psi] Nozzle orifice: 0.017-0.019"
Air spray	5%	Not Applicable.
Brush	5%	Not Applicable.

If brush or roller application is used, more coats will be necessary to achieve the specified dry film thickness. Spray data are indicative and subject to adjustment. Pressure is for a material temperature of 20°C [68°F].

Film thickness

Specification range	Low	High	Recommended
Dry film thickness	30 micron [1.2 mils]	40 micron [1.6 mils]	35 micron [1.4 mils]
Wet film thickness	60 micron [2.5 mils]	75 micron [3 mils]	70 micron [2.5 mils]
Theoretical spreading rate	17 m ² /L [690 sq ft/US gal]	13 m ² /L [530 sq ft/US gal]	15 m ² /L [610 sq ft/US gal]

Product may be specified in another film thickness than indicated depending on purpose and area of use. This will alter spreading rate, drying and curing time and overcoating interval. For best performance, avoid excessive film thickness.

Application conditions

- Surface temperature must be above -10°C [14°F] during application and curing.
- To avoid condensation, apply on a clean and dry surface with a temperature that is at least 3°C [5°F] above the dew point.

Relative Humidity:

- Relative humidity must be below 85% during curing.
- Relative humidity must be below 85% during application.

Application remarks

- Two coats of the topcoat may be necessary to obtain full hiding power.

Hempel's Polyenamel 55102

Drying and overcoating

Product compatibility

- Previous coat: None or according to Hempel's specification.
Recommended product is: Hempadur
- Subsequent coat: None.

Drying time

Surface temperature		20°C [68°F]
Surface dry	min	120
Hard dry	hours	4

Determined for dry film thickness 35 micron [1.4 mils] at standard conditions, see Hempel's Explanatory Notes for details.

Drying conditions

- To obtain the drying time stated, it is important to maintain sufficient ventilation during application, drying and curing.
- Condensation on the freshly applied coating should be avoided.

Overcoating details

- The surface must be clean before overcoating.

Other remarks

- Hempel's Specification supersedes any recommendations given in the Product Data Sheets.

Storage

Shelf life

Ambient temperature	25°C [77°F]	35°C [95°F]
Base	36 months	24 months
Curing agent	12 months	9 months

Shelf life from date of production, when stored in original, unopened containers. Thereafter, the product quality must be re-inspected. Always check the best before date or expiry date on the label.

Storage conditions

- The curing agent is sensitive to moisture. Store in a dry place and keep the can tightly closed until use.

Additional documents

Additional information is available at the Hempel website hempel.com or at your local Hempel website:

- Explanatory Notes explaining the fields in this Product Data Sheet.
- Surface Preparation Guidelines.
- Application Guidelines for different application methods.
- General Application Guidelines

This Product Data Sheet ("PDS") relates to the supplied product ("Product") and is subject to updating from time-to-time. Accordingly, the buyer/applicator should have regard to the PDS supplied together with the relevant batch of the Product (and not an earlier version). In addition to the PDS, the buyer/applicator may receive some or all of the following specifications, statements and/or guidelines as listed below or as are available from the Hempel website under 'Products' at www.hempel.com (the "Additional documents"):

No.	Document description	Location/comments
1.	Technical Statement	One-off specific advice provided on request for specific projects
2.	Specification	Only issued for specific projects
3.	PDS	This document
4.	Explanatory Notes to the PDS	Available at www.hempel.com and contain relevant information about the Product testing parameters
5.	Application Instruction	Where available, at www.hempel.com
6.	Generic technical guidelines (e.g. on application and surface preparation)	Where available, at www.hempel.com

In the event of a conflict of information between the PDS and the Additional documents, the order of priority of information shall be in the order as set out above. In such event you should also contact your representative at Hempel for clarification. Furthermore, the buyer/applicator must have full regard to the relevant Safety Data Sheet provided with each Product and which can also be downloaded from www.hempel.com.

Hempel shall not be liable for defects where the application of the Product has not been made fully in accordance with the recommendations and requirements set out in the relevant PDS and the Additional Documents. The information and terms of this disclaimer apply to this PDS, the Additional documents and any other documents supplied by Hempel in respect of the Product. In addition, the Product is supplied and all technical assistance is given subject to Hempel's General Conditions of Sale, Delivery and Service, unless otherwise expressly agreed in writing.