

# Versiline CUI

## Product characteristics

### Description

Versiline CUI 56990 is a MIO pigmented, fibre reinforced, inorganic co-polymer coating that cures to an inert polymer matrix, able to resist temperatures up to 650°C [1200°F] and thermal shock/cycling in dry or dry/wet service.

Conforms to NACE SP0198 - 2017 systems SS-5, CS-6 and CS-8. Approved to Saudi Aramco APCS-11C.

### Recommended use

Versiline CUI 56990 is recommended for long term protection of hot pipework, equipment and other hot surfaces. The product is specially developed to prevent corrosion under insulation (CUI) and is applied directly onto the steel substrate or over a zinc silicate primer.

### Service temperature:

- From -196°C [-321°F] up to 650°C [1202°F] for dry or dry/wet exposure.

### Certificates / Approvals

- Tested and assessed according to NACE TM0174; standard test method for evaluating protective coatings for immersion service. Resistance to Boiling Tap Water, Method B.
- Tested and assessed according to standard for Fire Test on Building Materials and Structures; method of test for ignitability BS 476-5.
- Tested and assessed according to standard for Fire Test on Building Materials and Structures; determination of the surface spread of flame of products BS 476-7.

### Features

- MIO pigmented.
- Able to resist temperatures up to 650°C [1200°F] and thermal shock/cycling in dry or dry/wet service.
- Prevents corrosion under insulation (CUI).
- Applied directly onto the steel substrate or over a zinc silicate primer.

## Product safety

**Flash point** 35°C [95°F]

## VOC content

Legislation	Value
EU	391 g/L [3.26 lb/US gal]
US (coatings)	391 g/L [3.26 lb/US gal]
US (regulatory)	391 g/L [3.26 lb/US gal]
China	391 g/L [3.26 lb/US gal]

According to specific legislation, see details in the Explanatory Notes available at Hempel website, [hempel.com](http://hempel.com) or at your local Hempel website. Measured according to GB/T 23985-2009. VOC values may vary with shade, please consult the Safety Data Sheet, section 9.

### Handling

Handle with care. Before and during use, observe safety labels on packaging and paint containers and follow all local and national safety regulations. Always consult Hempel's Safety Data Sheet for this product along with the Product Data Sheet.

For professional use only.

## Product data

### Product code

56990

### Standard shade / code

Metallic dark grey 10710 \*

### Gloss

Flat

### Volume solids

75 ± 2%

### Specific gravity

1.9 kg/L [16 lb/US gal]

### Reference dry film thickness

150 micron [5.9 mils]

# Versiline CUI

**Aluminium shade / code**

Pearlescent grey 19360

**Gloss**

Please consult Hempel's Guideline on aluminium pigmented coatings.

**Volume solids**

70 ± 2%

**Specific gravity**

1.8 kg/L [15 lb/US gal]

**Reference dry film thickness**

150 micron [5.9 mils]

## Surface preparation

**Cleanliness**

- Remove oil, grease and other contaminants by suitable detergent cleaning.
- Remove salts, detergents and other contaminants by high pressure fresh water cleaning.

**New build:**

- Abrasive blasting to min. Sa 2½ (ISO 8501-1) / SP 10 (SSPC).
- Remove dust, blast media and loose materials.
- Stainless steel, aluminium and other non ferric metals and alloys: use non-metallic blast media (corundum, garnet, etc.).

**Maintenance and Repair**

- Spot abrasive blasting to min. PSa 2½ (ISO 8501-2) / SP 10 (SSPC).
- Water jetting to Wa 2½ (ISO 8501-4).
- Flash rust degree of maximum FR M (ISO 8501-4).
- Minor areas may be hand or power tool cleaned instead of abrasive blasting.
- Remove dust, blast media and loose materials.
- Abrasive blasting to min. Sa 2½ (ISO 8501-1) / SP 10 (SSPC).
- Minor areas can be cleaned by power tool to St 2 provided the surface is roughened and not polished.
- Clean thoroughly by hand or power tool to St 3 (ISO 8501-1) / SP 3 (SSPC). Avoid polishing.

**Roughness**

- Surface profile Medium (G) (ISO 8503-2).

Consult Hempel's separate Surface Preparation Guidelines for more details.

## Application

**Mixing ratio**

Stir well before use.

**Thinner**

Hempel's Thinner 08080

**Cleaner**

Hempel's Thinner 08080

Hempel's Tool Cleaner 99610

**Application method**

Tool	Thinning max vol.	Application parameters
Airless spray	10%	Nozzle pressure: 175 bar [2500 psi] Nozzle orifice: 0.017-0.021"
Air spray	10%	Not Applicable.
Brush	5%	Not Applicable.

If brush or roller application is used, more coats will be necessary to achieve the specified dry film thickness. Spray data are indicative and subject to adjustment. Pressure is for a material temperature of 20°C [68°F].

# Versiline CUI

## Film thickness

Specification range	Low	High	Recommended
Dry film thickness	125 micron [4.9 mils]	225 micron [8.9 mils]	150 micron [5.9 mils]
Wet film thickness	170 micron [7 mils]	300 micron [12 mils]	200 micron [8 mils]
Theoretical spreading rate	6 m <sup>2</sup> /L [240 sq ft/US gal]	3.3 m <sup>2</sup> /L [130 sq ft/US gal]	5 m <sup>2</sup> /L [200 sq ft/US gal]

Product may be specified in another film thickness than indicated depending on purpose and area of use. This will alter spreading rate, drying and curing time and overcoating interval. For best performance, avoid excessive film thickness. Overthickness should be closely controlled and never locally exceed 225 micron [8.9 mils] DFT. On irregular surfaces it is recommended to employ special care in avoiding over application.

## Application conditions

- To avoid condensation, apply on a clean and dry surface with a temperature that is at least 3°C [5°F] above the dew point.
- Surface temperature must be above 10°C [50°F] during application and curing.
- Can be applied onto hot substrate up to maximum 200°C [392°F].

## Relative Humidity:

- Relative humidity must be below 85% during application.

## Drying and overcoating

### Product compatibility

- Previous coat: None or according to Hempel's specification. Recommended products are: Hempel's Galvosil 15700, Hempel's Galvosil 15680, Hempel's Galvosil Fibre 15750.
- Subsequent coat: None or according to Hempel's specification. Recommended products are: Hempel's Silicone Topcoat 56900, Hempel's Silicone Acrylic 56940, Hempel's Silicone Aluminium 56910.

## Drying time

Surface temperature		10°C [50°F]	20°C [68°F]	30°C [86°F]	40°C [104°F]
Touch dry	min	90	45	30	30
Hard dry	hours	4	2	1½	1½

Determined for dry film thickness 150 micron [5.9 mils] at standard conditions, see Hempel's Explanatory Notes for details.

## Overcoating

Hempel's specification supersedes any guidelines indicated in the overcoating table

Quality name		10°C [50°F]	20°C [68°F]	30°C [86°F]	40°C [104°F]
Atmospheric medium					
Versiline CUI	Min	18 h	6 h	3 h	2½ h
	Max	Ext*	Ext	Ext	Ext

Consult Hempel's specification for more information.

## Drying conditions

- To obtain the drying time stated, it is important to maintain sufficient ventilation during application, drying and curing.

## Overcoating details

- The surface must be dry and clean prior to application.

## Other remarks

- Hempel's Specification supersedes any recommendations given in the Product Data Sheets.

## Storage

### Shelf life

Ambient temperature	25°C [77°F]	35°C [95°F]
Product	12 months	9 months

Shelf life from date of production, when stored in original, unopened containers. Thereafter, the product quality must be re-inspected. Always check the best before date or expiry date on the label.

# Versiline CUI

## Storage conditions

- Product must be stored according to local legislation, at maximum 40°C [104°F], without direct sunlight and protected from rain and snow.

## Additional documents

Additional information is available at the Hempel website [hempel.com](http://hempel.com) or at your local Hempel website:

- Explanatory Notes explaining the fields in this Product Data Sheet.
- Surface Preparation Guidelines.
- Application Guidelines for different application methods.
- General Application Guidelines

This Product Data Sheet ("PDS") relates to the supplied product ("Product") and is subject to updating from time-to-time. Accordingly, the buyer/applicator should have regard to the PDS supplied together with the relevant batch of the Product (and not an earlier version). In addition to the PDS, the buyer/applicator may receive some or all of the following specifications, statements and/or guidelines as listed below or as are available from the Hempel website under 'Products' at [www.hempel.com](http://www.hempel.com) (the "Additional documents"):

No.	Document description	Location/comments
1.	Technical Statement	One-off specific advice provided on request for specific projects
2.	Specification	Only issued for specific projects
3.	PDS	This document
4.	Explanatory Notes to the PDS	Available at <a href="http://www.hempel.com">www.hempel.com</a> and contain relevant information about the Product testing parameters
5.	Application Instruction	Where available, at <a href="http://www.hempel.com">www.hempel.com</a>
6.	Generic technical guidelines (e.g. on application and surface preparation)	Where available, at <a href="http://www.hempel.com">www.hempel.com</a>

In the event of a conflict of information between the PDS and the Additional documents, the order of priority of information shall be in the order as set out above. In such event you should also contact your representative at Hempel for clarification. Furthermore, the buyer/applicator must have full regard to the relevant Safety Data Sheet provided with each Product and which can also be downloaded from [www.hempel.com](http://www.hempel.com).

Hempel shall not be liable for defects where the application of the Product has not been made fully in accordance with the recommendations and requirements set out in the relevant PDS and the Additional Documents. The information and terms of this disclaimer apply to this PDS, the Additional documents and any other documents supplied by Hempel in respect of the Product. In addition, the Product is supplied and all technical assistance is given subject to Hempel's General Conditions of Sale, Delivery and Service, unless otherwise expressly agreed in writing.