

PRODUCT DESCRIPTION A two pack epoxy finish.

INTENDED USES As a cosmetic finish coat for use on areas above the waterline.
For use at Newbuilding, Maintenance & Repair or On Board Maintenance.

| | | |
|----------------------------|-------------------------------|--|
| PRODUCT INFORMATION | Colour | ECB000-White, ECK724-Storm Grey, ECL274-Red, ECL549-Signal Green, ECY999-Black ; and a wide range of colours |
| | Finish/Sheen | High Gloss |
| | Converter/Curing Agent | ECA914 |
| | Volume Solids | 51% ±3% (ISO 3233:1998) |
| | Mix Ratio | 4.00 volumes Part A to 1 volume Part B |
| | Typical Film Thickness | 50 microns dry (98 microns wet) |
| | Theoretical Coverage | 10.20 (m ² /lt) at 40 microns dry and 51% volume solids, allow appropriate loss factor |
| | Method of Application | Airless Spray, Brush, Conventional Spray, Roller |
| | Flash Point | Part A 27°C ; Part B 29°C ; Mixed 28°C |
| | Induction Period | 30 minutes at temperatures below 25°C |

Drying Information

| | 5°C | 10°C | 25°C | 35°C |
|-------------------------|-------|-------|-------|-------|
| Touch Dry [ISO 1517:73] | 16hrs | 12hrs | 3hrs | 2hrs |
| Hard Dry [ISO 9117:90] | 54hrs | 40hrs | 16hrs | 12hrs |
| Pot Life | 12hrs | 11hrs | 8hrs | 3hrs |

Overcoating Data - see limitations

| | Substrate Temperature | | | | | | | |
|---------------|------------------------------|-----|-------|-----|-------|-----|-------|-----|
| | 5°C | | 10°C | | 25°C | | 35°C | |
| Overcoated By | Min | Max | Min | Max | Min | Max | Min | Max |
| Intergard 740 | 54hrs | ext | 40hrs | ext | 16hrs | ext | 12hrs | ext |

| | | |
|------------------------|------------|--|
| REGULATORY DATA | VOC | 420 g/lt as supplied (EPA Method 24) 344 g/kg EU Solvent Emissions Directive (Council Directive 1999/13/EC) |
|------------------------|------------|--|

CERTIFICATION

When used as part of an approved scheme, this material has the following certification:

- Food Contact - Carriage of Grain (NOHA)
- Fire Resistance - Surface Spread of Flame (WFR) - (IMO Resolution A653 (16))
- Fire Resistance - MSC61 (67) Smoke & Toxicity (WFR)
- Fire Resistance - Marine Equipment Directive compliant

Consult your International Paint representative for details.

SYSTEMS AND COMPATIBILITY

Intergard 740 should only be applied over epoxy anticorrosive primers. The primer to be used will depend upon vessel area and application location. Typical primers include:

Interbond 201
Intergard 269 (as a tiecoat over Interzinc 22 on external decks)
Intergard 400
Intergard 264
Intershield 300
Intershield 803
Intertuf 262
Intertuf 362

Consult your International Paint representative for the system best suited for the surfaces to be protected.

SURFACE PREPARATIONS

Use in accordance with the standard Worldwide Marine Specifications.

All surfaces to be coated should be clean, dry and free from contamination.

High pressure fresh water wash or fresh water wash, as appropriate, and remove all oil or grease, soluble contaminants and other foreign matter in accordance with SSPC-SP1 solvent cleaning.

NEWBUILDING/MAJOR REFURBISHMENT

Intergard 740 should always be applied over a recommended primer coating scheme. The primer surface should be dry and free from all contamination, and Intergard 740 must be applied within the overcoating intervals specified (consult the relevant product data sheet). Areas of breakdown, damage etc. should be prepared to the specified standard (eg. Sa2½ (ISO 8501-1 : 1988)) and primed prior to the application of Intergard 740.

REPAIR/OBM

Intergard 740 should always be applied over a recommended primer coating scheme. The primer surface should be dry and free from all contamination, and Intergard 740 must be applied within the overcoating intervals specified (consult the relevant product data sheet). Areas of breakdown, damage etc. should be prepared to the specified standard (eg. Sa2½ (ISO 8501-1 : 1988)) and primed prior to the application of Intergard 740.

Intergard 740 may be applied directly over aged Intergard 740 following thorough fresh water washing and degreasing provided the coating to be overcoated is in an intact and tightly adherent condition. Loose or flaking coatings should be removed back to a firm edge and Intergard 740 or an appropriate primer should be used to repair the area before application of the full coat.

Consult your International Paint representative for specific recommendations.

NOTE:

For use in Marine situations in North America, the following surface preparation standards can be used: SSPC-SP10 in place of Sa2½ (ISO 8501-1:1988)

APPLICATION

| | |
|-----------------------------------|---|
| Mixing | Material is supplied in 2 containers as a unit. Always mix a complete unit in the proportions supplied. (1) Agitate Base (Part A) with a power agitator. (2) Combine entire contents of Curing Agent (Part B) with Base (Part A) and mix thoroughly with power agitator. |
| Thinner | Not recommended. Use International GTA220 only in exceptional circumstances (max 5% by volume). DO NOT thin more than allowed by local environmental legislation. |
| Airless Spray | Recommended. - Tip range 0.38 - 0.53mm (15-21 thou) - Total output fluid pressure at spray tip not less than 176 kg/cm ² (2500 p.s.i.) |
| Conventional Spray | Use suitable proprietary equipment. Thinning may be required. |
| Brush | Application by brush is recommended for small areas only. Multiple coats may be required to achieve specified film thickness. |
| Roller | Application by roller is recommended for small areas only. Multiple coats may be required to achieve specified film thickness. |
| Cleaner | International GTA822 or International GTA220 (USA) |
| Work Stoppages and Cleanup | Do not allow material to remain in hoses, gun or spray equipment. Thoroughly flush all equipment with International GTA822 or International GTA220 (USA). Once units of paint have been mixed they should not be resealed and it is advised that after prolonged stoppages work recommences with freshly mixed units. Clean all equipment immediately after use with International GTA822 or International GTA220 (USA). It is good working practice to periodically flush out spray equipment during the course of the working day. Frequency of cleaning will depend upon amount sprayed, temperature and elapsed time, including any delays. Do not exceed pot life limitations. All surplus materials and empty containers should be disposed of in accordance with appropriate regional regulations/legislation. |
| Welding | In the event welding or flame cutting is performed on metal coated with this product, dust and fumes will be emitted which will require the use of appropriate personal protective equipment and adequate local exhaust ventilation. In North America do so in accordance with instruction in ANSI/ASC Z49.1 "Safety in Welding and Cutting." |

SAFETY

All work involving the application and use of this product should be performed in compliance with all relevant national Health, Safety & Environmental standards and regulations.

Prior to use, obtain, consult and follow the Material Safety Data Sheet for this product concerning health and safety information. Read and follow all precautionary notices on the Material Safety Data Sheet and container labels. If you do not fully understand these warnings and instructions or if you can not strictly comply with them, do not use this product. Proper ventilation and protective measures must be provided during application and drying to keep solvent vapour concentrations within safe limits and to protect against toxic or oxygen deficient hazards. Take precautions to avoid skin and eye contact (ie. gloves, goggles, face masks, barrier creams etc.) Actual safety measures are dependant on application methods and work environment.

EMERGENCY CONTACT NUMBERS:
USA/Canada - Medical Advisory Number 1-800-854-6813
Europe - Contact (44) 191 4696111. For advice to Doctors & Hospitals only contact (44) 207 6359191
R.O.W. - Contact Regional Office (see page 4 of Data Sheet)

LIMITATIONS

This product will not cure adequately below 5°C (41°F). For maximum performance ambient curing temperatures should be above 10°C (50°F).
In common with all epoxy based coatings Intergard 740 will exhibit chalking of the film on UV exposure. Overcoating information is given for guidance only and is subject to regional variation depending upon local climate and environmental conditions. Consult your local International Paint representative for specific recommendations. Apply in good weather. Temperature of the surface to be coated must be at least 3°C (5°F) above the dew point. For optimum application properties bring the material to 21-27°C (70-80°F), unless specifically instructed otherwise, prior to mixing and application. Unmixed material (in closed containers) should be maintained in protected storage in accordance with information given in the STORAGE Section of this data sheet. Technical and application data herein is for the purpose of establishing a general guideline of the coating application procedures. Test performance results were obtained in a controlled laboratory environment and International Paint makes no claim that the exhibited published test results, or any other tests, accurately represent results found in all field environments. As application, environmental and design factors can vary significantly, due care should be exercised in the selection, verification of performance and use of the coating.
In the overcoating data section 'ext' = extended overcoating period. Please refer to our Marine Painting Guide - Definitions and Abbreviations available on our website.

UNIT SIZE

20 litre unit: Intergard 740, Part A, 16 litres in a 20 litre container and Part B, 4 litres in a 5 litre container.
1 US gallon unit (3.79 lt) : Intergard 740, Part A, 0.8 US gallon in a 1 US gallon container and Part B, 0.2 US gallon in a 1 US quart container.
5 US gallon unit : Intergard 740, Part A, 4 US gallons in a 5 US gallon container and Part B, 1 US gallon in a 1 US gallon container
For availability of other unit sizes consult International Paint.

UNIT SHIPPING WEIGHT

20 litre unit: 29.00 kg
1 US gallon unit (3.79 lt) - 13.1 lb (6.0 kg)
5 US gallon unit (18.93 lt) - 64.5 lb (29.3 kg)

STORAGE


Shelf Life
12 months minimum at 25°C (77°F). Subject to re-inspection thereafter. Store in dry, shaded conditions away from sources of heat and ignition.

WORLDWIDE AVAILABILITY

Consult International Paint.

IMPORTANT NOTE

The information in this data sheet is not intended to be exhaustive: any person using the product for any purpose other than that specifically recommended in this data sheet without first obtaining written confirmation from us as to the suitability of the product for the intended purpose does so at his own risk. All advice we give or statements made about the product (whether in this data sheet or otherwise) is correct to the best of our knowledge but we have no control over the quality or the condition of the substrate or the many factors affecting the use and application of the product. Therefore, unless we specifically agree in writing to do so, we do not accept any liability at all for the performance of the product or for (subject to law) any loss or damage arising out of the use of the product. All products supplied and technical advice given are subject to our standard terms and conditions of sale. You should request a copy of this document and review it carefully. The information contained in this data sheet is liable to modification from time to time in the light of experience and our policy of continuous development. It is the user's responsibility to check that this data sheet is current prior to using the product. It is the user's responsibility to check with his local International Paint representative that this data sheet is current prior to using the product.

 and product names mentioned in this data sheet are trademarks of or are licensed to Akzo Nobel.
© Akzo Nobel, 2004

Worldwide Operations

Argentina, Australia, Bahrain, Belgium, Brazil, Bulgaria, Canada, Chile, Colombia, Croatia, Cuba, Cyprus, Denmark, Ecuador, Egypt, Estonia, Fiji, Finland, France, Germany, Greece, Hong Kong, Iceland, India, Indonesia, Iran, Italy, Japan, Kuwait, Latvia, Lithuania, Luxembourg, Malaysia, Malta, Mexico, Netherlands, New Zealand, Northern Ireland, Norway, Pakistan, Panama, Papua New Guinea, Peoples Republic of China, Peru, Philippines, Poland, Portugal, Qatar, Republic of Ireland, Romania, Russia, Saudi Arabia, Singapore, Slovenia, South Africa, South Korea, Spain, Sri Lanka, Sweden, Taiwan, Thailand, Turkey, U.S.A., Ukraine, United Arab Emirates, United Kingdom, Uruguay, Venezuela, Vietnam, Western Samoa, Yemen

Head Office

International Paint Ltd, Oriel House, 16 Connaught Place, London W2 2ZB, United Kingdom, Tel: +44 (0) 207 479 6000, Fax: +44 (0) 207 479 6500

www.international-marine.com