

SIGMA ECOFLEET® 530

DESCRIPTION

High-activity, self-polishing antifouling, for extreme and aggressive fouling conditions

PRINCIPAL CHARACTERISTICS

- TBT-free self-polishing antifouling for new-building and maintenance
- Controls shell and weed fouling for service periods up to 60 months, depending on vessel type, operation characteristics and system applied
- Controlled polishing rate to give effective protection in accordance with the specified film thickness and smoothing of the surface
- Complies with IMO Antifouling Systems Convention

COLOR AND GLOSS LEVEL

- Redbrown, brown, black, blue, spruce
- Flat

BASIC DATA AT 20°C (68°F)

| Data for product | |
|--------------------------------|--|
| Number of components | One |
| Mass density | 2.0 kg/l (16.7 lb/US gal) |
| Volume solids | 60 ± 2% |
| VOC (Supplied) | Directive 1999/13/EC, SED: max. 173.0 g/kg max. 339.0 g/l (approx. 2.8 lb/US gal) |
| Recommended dry film thickness | 75 - 150 µm (3.0 - 6.0 mils) depending on system |
| Theoretical spreading rate | 8.0 m²/l for 75 µm (321 ft²/US gal for 3.0 mils) |
| Dry to touch | 1 hour |
| Overcoating Interval | Minimum: 6 hours |
| Refloating time | Minimum: 8 hours |
| Shelf life | At least 18 months when stored cool and dry |

Notes:

- See ADDITIONAL DATA – Spreading rate and film thickness
- See ADDITIONAL DATA – Overcoating intervals

RECOMMENDED SUBSTRATE CONDITIONS AND TEMPERATURES

Substrate conditions

- Suitable high performance anticorrosive tiecoats
- Previous coat must be sound, dry and free from any contamination



**PPG Protective &
Marine Coatings**

Bringing innovation to the surface.™

SIGMA ECOFLEET® 530

Substrate temperature and application conditions

- Substrate temperature during application should be at least 3°C (5°F) above dew point
-

INSTRUCTIONS FOR USE

- Stir well before use
 - The temperature of the paint should preferably be above 15°C (59°F), otherwise extra thinner may be required to obtain application viscosity
 - Adding too much thinner results in reduced sag resistance
-

Airless spray**Recommended thinner**

THINNER 21-06

Volume of thinner

0 - 3%, depending on required thickness and application conditions

Nozzle orifice

Approx. 0.53 – 0.69 mm (0.021 – 0.027 in)

Nozzle pressure12.0 - 15.0 MPa (approx. 120 - 150 bar; 1741 - 2176 p.s.i.)

Brush/roller

- Only for touch-up and repair

Recommended thinner

THINNER 21-06

Volume of thinner0 – 3%

Cleaning solventTHINNER 21-06

SIGMA ECOFLEET® 530

ADDITIONAL DATA

| Spreading rate and film thickness | |
|-----------------------------------|---|
| DFT | Theoretical spreading rate |
| 75 µm (3.0 mils) | 8.0 m ² /l (321 ft ² /US gal) |
| 100 µm (4.0 mils) | 6.0 m ² /l (241 ft ² /US gal) |
| 150 µm (6.0 mils) | 4.0 m ² /l (160 ft ² /US gal) |

| Overcoating interval for DFT up to 150 µm (6.0 mils) | | | | | |
|--|----------------------|------------|-------------|-------------|-------------|
| Overcoating with... | Interval | 5°C (41°F) | 10°C (50°F) | 20°C (68°F) | 30°C (86°F) |
| itself | Minimum | 18 hours | 12 hours | 6 hours | 4 hours |
| | Refloating - Minimum | 24 hours | 12 hours | 8 hours | 6 hours |

Notes:

- maximum overcoating time for SIGMACOVER 510 with Sigma EcoFleet 530 is 48 hours at 20°C
- the above data are a fair indication for normal dry dockings
- longer drying times may be necessary at higher dft and under unfavourable atmospheric conditions

SAFETY PRECAUTIONS

- For paint and recommended thinners see INFORMATION SHEETS 1430, 1431 and relevant Material Safety Data Sheets
- This is a solvent-borne paint and care should be taken to avoid inhalation of spray mist or vapor, as well as contact between the wet paint and exposed skin or eyes

WORLDWIDE AVAILABILITY

It is always the aim of PPG Protective and Marine Coatings to supply the same product on a worldwide basis. However, slight modification of the product is sometimes necessary to comply with local or national rules/circumstances. Under these circumstances an alternative product data sheet is used.

REFERENCES

| | | |
|--|-------------------|------|
| • EXPLANATION TO PRODUCT DATA SHEETS | INFORMATION SHEET | 1411 |
| • SAFETY INDICATIONS | INFORMATION SHEET | 1430 |
| • SAFETY IN CONFINED SPACES AND HEALTH SAFETY, EXPLOSION HAZARD – TOXIC HAZARD | INFORMATION SHEET | 1431 |

WARRANTY

PPG warrants (i) its title to the product, (ii) that the quality of the product conforms to PPG's specifications for such product in effect at the time of manufacture and (iii) that the product shall be delivered free of the rightful claim of any third person for infringement of any U.S. patent covering the product. THESE ARE THE ONLY WARRANTIES THAT PPG MAKES AND ALL OTHER EXPRESS OR IMPLIED WARRANTIES, UNDER STATUTE OR ARISING OTHERWISE IN LAW, FROM A COURSE OF DEALING OR USAGE OF TRADE, INCLUDING WITHOUT LIMITATION, ANY OTHER WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR USE, ARE DISCLAIMED BY PPG. Any claim under this warranty must be made by Buyer to PPG in writing within five (5) days of Buyer's discovery of the claimed defect, but in no event later than the expiration of the applicable shelf life of the product, or one year from the date of the delivery of the product to the Buyer, whichever is earlier. Buyer's failure to notify PPG of such non-conformance as required herein shall bar Buyer from recovery under this warranty.

SIGMA ECOFLEET® 530

LIMITATIONS OF LIABILITY

IN NO EVENT WILL PPG BE LIABLE UNDER ANY THEORY OF RECOVERY (WHETHER BASED ON NEGLIGENCE OF ANY KIND, STRICT LIABILITY OR TORT) FOR ANY INDIRECT, SPECIAL, INCIDENTAL, OR CONSEQUENTIAL DAMAGES IN ANY WAY RELATED TO, ARISING FROM, OR RESULTING FROM ANY USE MADE OF THE PRODUCT. The information in this sheet is intended for guidance only and is based upon laboratory tests that PPG believes to be reliable. PPG may modify the information contained herein at any time as a result of practical experience and continuous product development. All recommendations or suggestions relating to the use of the PPG product, whether in technical documentation, or in response to a specific inquiry, or otherwise, are based on data, which to the best of PPG's knowledge, is reliable. The product and related information is designed for users having the requisite knowledge and industrial skills in the industry and it is the end-user's responsibility to determine the suitability of the product for its own particular use and it shall be deemed that Buyer has done so, as its sole discretion and risk. PPG has no control over either the quality or condition of the substrate, or the many factors affecting the use and application of the product. Therefore, PPG does not accept any liability arising from any loss, injury or damage resulting from such use or the contents of this information (unless there are written agreements stating otherwise). Variations in the application environment, changes in procedures of use, or extrapolation of data may cause unsatisfactory results. This sheet supersedes all previous versions and it is the Buyer's responsibility to ensure that this information is current prior to using the product. Current sheets for all PPG Protective & Marine Coatings Products are maintained at www.ppgpmc.com. The English text of this sheet shall prevail over any translation thereof.

Depending on specific country of application the following versions are available:

| Article code | Color | Reference |
|--------------|----------|------------|
| 146095 | redbrown | 2008002200 |
| 146096 | brown | 2000002200 |
| 180438 | black | 8000002200 |
| 230906 | blue | 1000002200 |
| 164865 | spruce | 1645302200 |

The PPG Logo, Bringing innovation to the surface., and all other trademarks herein are property of the PPG group of companies.