

# SIGMARINE™ 24

## DESCRIPTION

Modified zinc phosphate alkyd primer

## PRINCIPAL CHARACTERISTICS

- Economical, general-purpose maintenance and new-building primer
- Suitable for use on superstructures and on steel surfaces not normally exposed to water immersion
- The adhesion of subsequent coats is not affected by long weathering periods of the primer
- Should not be used over zinc primers, except when exposed to dry interior conditions
- To be recoated with conventional paint systems
- A thickness of 75 µm (3.0 mils) can be obtained by spray application in one operation by means of the cross-coat technique

## COLOR AND GLOSS LEVEL

- Yellow, brown, red, gray, dark gray (offwhite only on request)
- Flat

## BASIC DATA AT 20°C (68°F)

Data for product	
Number of components	One
Mass density	1.4 kg/l (11.7 lb/US gal)
Volume solids	56 ± 2%
VOC (Supplied)	Directive 1999/13/EC, SED: max. 245.0 g/kg max. 343.0 g/l (approx. 2.9 lb/US gal)
Recommended dry film thickness	35 - 75 µm (1.4 - 3.0 mils) per coat
Theoretical spreading rate	16.0 m²/l for 35 µm (642 ft²/US gal for 1.4 mils) 7.5 m²/l for 75 µm (299 ft²/US gal for 3.0 mils)
Dry to touch	2 hours
Overcoating Interval	Minimum: 24 hours Maximum: Unlimited
Shelf life	At least 24 months when stored cool and dry

### Notes:

- See ADDITIONAL DATA – Spreading rate and film thickness
- See ADDITIONAL DATA – Curing time



# SIGMARINE™ 24

## RECOMMENDED SUBSTRATE CONDITIONS AND TEMPERATURES

### Substrate conditions

- Steel; blast cleaned to ISO-Sa2½, blasting profile 40 – 70 µm (1.6 – 2.8 mils)
  - Steel; power tool cleaned to min. ISO-St2
  - Shop primed steel; sweep blasted or power tool cleaned to SPSS-Ss or SPSS-Pt2
  - Previous coat must be dry and free from any contamination
- 

### Substrate temperature and application conditions

- Substrate temperature during application should not exceed 50°C (122°F)
  - Substrate temperature during application should be at least 3°C (5°F) above dew point
- 

## SYSTEM SPECIFICATION

- SYSTEMS FOR BOOTTOP AND TOPSIDE – SYSTEM SHEET 3102
  - SYSTEMS FOR DECKS – SYSTEM SHEET 3103
  - SYSTEMS FOR SUPERSTRUCTURE AND DECK FITTINGS – SYSTEM SHEET 3104
  - SYSTEMS FOR INTERIOR(S) – SYSTEM SHEET 3105
- 

## INSTRUCTIONS FOR USE

- Stir well before use
  - The temperature of the paint should preferably be above 15°C (59°F), otherwise extra thinner may be required to obtain application viscosity
  - Adding too much thinner results in reduced sag resistance
  - Adequate ventilation must be maintained during application and curing (please refer to INFORMATION SHEETS 1433 and 1434)
- 

### Airless spray

#### **Recommended thinner**

THINNER 20-05

#### **Volume of thinner**

0 - 3%, depending on required thickness and application conditions

#### **Nozzle orifice**

Approx. 0.43 – 0.48 mm (0.017 – 0.019 in)

#### **Nozzle pressure**

12.0 - 15.0 MPa (approx. 120 - 150 bar; 1741 - 2176 p.s.i.)

---

# SIGMARINE™ 24

**Brush/roller****Recommended thinner**

THINNER 20-05

**Volume of thinner**

0 – 2%

**Cleaning solvent**

THINNER 20-05

**ADDITIONAL DATA****Spreading rate and film thickness**

DFT	Theoretical spreading rate
35 µm (1.4 mils)	16.0 m <sup>2</sup> /l (642 ft <sup>2</sup> /US gal)
75 µm (3.0 mils)	7.5 m <sup>2</sup> /l (299 ft <sup>2</sup> /US gal)

**Curing time for DFT up to 75 µm (3.0 mils)**

Substrate temperature	Dry to touch
5°C (41°F)	3 hours
20°C (68°F)	2 hours

**SAFETY PRECAUTIONS**

- For paint and recommended thinners see INFORMATION SHEETS 1430, 1431 and relevant Material Safety Data Sheets
- This is a solvent-borne paint and care should be taken to avoid inhalation of spray mist or vapor, as well as contact between the wet paint and exposed skin or eyes

**WORLDWIDE AVAILABILITY**

It is always the aim of PPG Protective and Marine Coatings to supply the same product on a worldwide basis. However, slight modification of the product is sometimes necessary to comply with local or national rules/circumstances. Under these circumstances an alternative product data sheet is used.



# SIGMARINE™ 24

REFERENCES

• CONVERSION TABLES	INFORMATION SHEET	1410
• EXPLANATION TO PRODUCT DATA SHEETS	INFORMATION SHEET	1411
• SAFETY INDICATIONS	INFORMATION SHEET	1430
• SAFETY IN CONFINED SPACES AND HEALTH SAFETY, EXPLOSION HAZARD – TOXIC HAZARD	INFORMATION SHEET	1431
• SAFE WORKING IN CONFINED SPACES	INFORMATION SHEET	1433
• DIRECTIVES FOR VENTILATION PRACTICE	INFORMATION SHEET	1434
• CLEANING OF STEEL AND REMOVAL OF RUST	INFORMATION SHEET	1490
• SPECIFICATION FOR MINERAL ABRASIVES	INFORMATION SHEET	1491
• RELATIVE HUMIDITY – SUBSTRATE TEMPERATURE – AIR TEMPERATURE	INFORMATION SHEET	1650

WARRANTY

PPG warrants (i) its title to the product, (ii) that the quality of the product conforms to PPG’s specifications for such product in effect at the time of manufacture and (iii) that the product shall be delivered free of the rightful claim of any third person for infringement of any U.S. patent covering the product. THESE ARE THE ONLY WARRANTIES THAT PPG MAKES AND ALL OTHER EXPRESS OR IMPLIED WARRANTIES, UNDER STATUTE OR ARISING OTHERWISE IN LAW, FROM A COURSE OF DEALING OR USAGE OF TRADE, INCLUDING WITHOUT LIMITATION, ANY OTHER WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR USE, ARE DISCLAIMED BY PPG. Any claim under this warranty must be made by Buyer to PPG in writing within five (5) days of Buyer’s discovery of the claimed defect, but in no event later than the expiration of the applicable shelf life of the product, or one year from the date of the delivery of the product to the Buyer, whichever is earlier. Buyer’s failure to notify PPG of such non-conformance as required herein shall bar Buyer from recovery under this warranty.

LIMITATIONS OF LIABILITY

IN NO EVENT WILL PPG BE LIABLE UNDER ANY THEORY OF RECOVERY (WHETHER BASED ON NEGLIGENCE OF ANY KIND, STRICT LIABILITY OR TORT) FOR ANY INDIRECT, SPECIAL, INCIDENTAL, OR CONSEQUENTIAL DAMAGES IN ANY WAY RELATED TO, ARISING FROM, OR RESULTING FROM ANY USE MADE OF THE PRODUCT. The information in this sheet is intended for guidance only and is based upon laboratory tests that PPG believes to be reliable. PPG may modify the information contained herein at any time as a result of practical experience and continuous product development. All recommendations or suggestions relating to the use of the PPG product, whether in technical documentation, or in response to a specific inquiry, or otherwise, are based on data, which to the best of PPG’s knowledge, is reliable. The product and related information is designed for users having the requisite knowledge and industrial skills in the industry and it is the end-user’s responsibility to determine the suitability of the product for its own particular use and it shall be deemed that Buyer has done so, as its sole discretion and risk. PPG has no control over either the quality or condition of the substrate, or the many factors affecting the use and application of the product. Therefore, PPG does not accept any liability arising from any loss, injury or damage resulting from such use or the contents of this information (unless there are written agreements stating otherwise). Variations in the application environment, changes in procedures of use, or extrapolation of data may cause unsatisfactory results. This sheet supersedes all previous versions and it is the Buyer’s responsibility to ensure that this information is current prior to using the product. Current sheets for all PPG Protective & Marine Coatings Products are maintained at [www.ppgpmc.com](http://www.ppgpmc.com). The English text of this sheet shall prevail over any translation thereof.

The PPG Logo, Bringing innovation to the surface., and all other trademarks herein are property of the PPG group of companies.