



Advanced Edge Glue Down LVP

Slip Resistance Testing

Test results meet ADA requirements and OSHA standards

Test Items		Test Results
Anti-slip (static friction rub coefficient)	Wet Method	.57
	Dry Method	.6