

Designation Thickness Mills	Minimum Thickness inch	Design Thickness inch	Gauge no (reference)
18	0.0179	0.0188	25
27	0.0269	0.0283	22
30	0.0296	0.0312	20 drywall
33	0.0329	0.0346	20-structural
43	0.0428	0.0451	18
54	0.0538	0.0566	16
68	0.0677	0.0713	14
97	0.0966	0.1017	12