



Sand

FICHA TÉCNICA

Technical Data Sheet

Cemento en acabado pulido
Polished concrete finish

60 X 120 CM.
24 X 48 IN.

Porcelanato esmaltado. Rectificado.
Glazed porcelain tile. Rectified.



4 Caras
4 Faces



Alto Tráfico
High Traffic



Variación Alta
High Variation



Pasta Blanca
White body

Uso Usage



Interior
Interior



Baño
Bathroom



Cocina
Kitchen

Porcelanato pulido / Polished porcelain tile

Características técnicas / Technical specifications

	Pasta blanca / White body		
	Separación de boquilla / Grout size	2 mm	
	PEI	4	
	Resistencia química / Chemical resistance	Conforme	ASTM C650
	DCOF / Dynamic Coefficient of Friction	>0.42	ASTM C1028
	Absorción de agua / Water absorption	≤0.5%	ASTM C373
	MOHS	5-8	ASTM C1028
	Resistencia de flexión / Breaking strength	>350 kg	ISO 10545-4
	Shock térmico / Thermal shock resistance	Conforme	ASTM C484
	Resistencia a helada / Frost resistance	Conforme	ASTM C1026
	Resistencia a manchas / Stain resistance	Conforme	ASTM C1378
	Resistencia de abrasión / Abrasion resistance	Conforme	ANSI A137



Información de Embalaje

PZS-CAJA / PCS-BOX	M ² -CAJA / FT ² -BOX	KG-CAJA / LBS-BOX
2	1.44 / 15.50	29.50 / 65.03

Cesantoni S.A. de C.V. certifica que los resultados anteriores fueron obtenidos en análisis de laboratorio elaborado por el departamento de Control de Calidad.

Cesantoni certifies that the above results were obtained in laboratory testing performed by the quality control department.

www.cesantoni.com.mx contacto@cesantoni.com.mx





Sand

FICHA TÉCNICA

Technical Data Sheet

Cemento en acabado mate / Matte concrete finish | 60 X 120 CM. / 24 X 48 IN. | Porcelanato esmaltado. Rectificado. / Glazed porcelain tile. Rectified.

4 Caras / 4 Faces |
 Alto Tráfico / High Traffic |
 Variación Alta / High Variation |
 Pasta Blanca / White body

Uso / Usage

Interior / Interior |
 Baño / Bathroom |
 Cocina / Kitchen |
 Exterior / Exterior |
 Comercial / Commercial

Porcelanato mate / Matte porcelain tile

Características técnicas / Technical specifications

	Pasta blanca / White body		
	Separación de boquilla / Grout size	2 mm	
	PEI	4	
	Resistencia química / Chemical resistance	Conforme	ASTM C650
	DCOF / Dynamic Coefficient of Friction	>0.42	ASTM C1028
	Absorción de agua / Water absorption	≤0.5%	ASTM C373
	MOHS	5-8	ASTM C1028
	Resistencia de flexión / Breaking strength	>350 kg	ISO 10545-4
	Shock térmico / Thermal shock resistance	Conforme	ASTM C484
	Resistencia a helada / Frost resistance	Conforme	ASTM C1026
	Resistencia a manchas / Stain resistance	Conforme	ASTM C1378
	Resistencia de abrasión / Abrasion resistance	Conforme	ANSI A137

Información de Embalaje	PZS-CAJA / PCS-BOX	M ² -CAJA / FT ² -BOX	KG-CAJA / LBS-BOX
	2	1.44 / 15.50	29.85 / 65.80

Cesantoni S.A. de C.V. certifica que los resultados anteriores fueron obtenidos en análisis de laboratorio elaborado por el departamento de Control de Calidad.

Cesantoni certifies that the above results were obtained in laboratory testing performed by the quality control department.

www.cesantoni.com.mx | contacto@cesantoni.com.mx

