




AGGREGATE GRADING ANALYSIS

Client: Smalldene Midlands Ltd

Sample Ref.	26.137
Source	Armoury Road, Small Heath
Material Description	0-6mm
Date of Sample	26th May 2026
Date of Test	3rd June 2026
Sample Weight	750

Sieve Size	Weight Retained	% Weight Retained	% Passing By Weight	Limits %	Pass/Fail
8.0mm	0.00	0.0%	100.0%	N/A	NA
6.0mm	0.00	0.0%	100.0%	N/A	N/A
4.0mm	43.00	5.7%	94.3%	N/A	N/A
2.0mm	127.00	16.9%	83.1%	N/A	N/A
1.0mm	195.00	26.0%	74.0%	N/A	N/A
500um	220.00	29.3%	70.7%	N/A	N/A
250um	443.00	59.1%	40.9%	N/A	N/A
63um	750.00	100.0%	0.0%	N/A	N/A
PAN	0.00	0.0%		N/A	N/A

Moisture %	6.30%
------------	-------



Signed

Dated

4th June 2026

			Tel: 07700 169325				
--	--	--	-------------------	--	--	--	--

