


AGGREGATE GRADING ANALYSIS

Client: Smalldene Midlands

Sample Ref.	26.131
Source	Armoury Road, Small Heath
Material Description	6F5
Date Sample Received	26th May 2026
Date of Test	3rd June 2026
Sample Weight (g)	3000

Sieve Size	Cum. Weight Retained	% Weight Retained	% Passing By Weight	Limits %	Pass/Fail
125mm	0.00	0.0%	100.0%	100	PASS
80mm	43.00	1.4%	98.6%	75-99	PASS
40mm	461.00	15.4%	84.6%	50-90	PASS
20mm	1607.00	53.6%	46.4%	30-75	PASS
10mm	2033.00	67.8%	32.2%	15-60	PASS
2mm	2428.00	80.9%	19.1%	0-35	PASS
0.063mm	2745.00	91.5%	8.5%	0-12	FAIL

Moisture %	4.20%
------------	-------



Signed



Dated

4th June 2026

on behalf of Albert Cole Consultants

100.0%	100.0%
75.0%	99.0%
50.0%	90.0%
30.0%	75.0%
15.0%	60.0%
0.0%	35.0%
0.0%	12.0%