			Cons	rt Cole sultants eesoils consultan	CY			
			ndon Road, Liphook, Hampshire GU30 7TB					
	AGGREGATE GRADING ANALYSIS							
	Client	Smalldene Midla	nds Ltd					
	Sample Ref. Source Material Description Date of Sample Date of Test		24.435 Armoury Road, Small Heath 4-10mm 3rd December 2024 12th December 2024					
	Sample Weig	ıht	750					
	Sieve	Cum. Weight	% Weight	% Passing	Limits %	Pass/		
	Size	Retained	Retained	By Weight		Fail		
	20.0mm	0.00	0.0%	100.0%	100	PASS		
	14.0mm	15.00	2.0%	98.0%	98-100	PASS		
	10.0mm	87.00	11.6%	88.4%	85-99	PASS		
	4.0mm	712.00	94.9%	5.1%	0-20	PASS		
	2.0mm	732.00	97.6%	2.4%	0-5	PASS		
	PAN	750.00	100.0%					
			Moisture %	4				
				·				
			Gra	ading Curve				
100.0%							_	
				7/			_	
75.0%								
7 0.0 70								
E0 00'								
50.0%				// /	\			
ວບ.ບ%				\\	\			
ou.0%								
50.0% 25.0%								
		14 0m;	m 10	J.Omm	4.0mm	2 0mm		
25.0%		n 14.0mi	m 10	0.0mm	4.0mm	2.0mm		
25.0%	20.0mm	n 14.0mi				2.0mm		
25.0%	20.0mm		BS EN 12620 gra	ading requirement				