

8 Lincoln Court, London Road, Liphook, Hampshire GU30 7TB

Tel: 0330 043 0523 Email: albert@albertcoleconsultants.co.uk


AGGREGATE GRADING ANALYSIS

Client Smaldene Midlands

Sample Ref.	26.134
Source	Armoury Road, Small Heath
Material Description	10-20mm
Date of Sample	26th May 2026
Date of Test	3rd June 2026
Sample Weight	1000

Sieve Size	Cum. Weight Retained	% Weight Retained	% Passing By Weight	Limits %	Pass/Fail
40.0mm	0.00	0.0%	100.0%	100	PASS
31.5mm	11.00	1.1%	98.9%	98-100	PASS
20.0mm	88.00	8.8%	91.2%	85-99	PASS
10.0mm	861.00	86.1%	13.9%	0-20	PASS
4.0mm	964.00	96.4%	3.6%	0-5	PASS
PAN	1000.00	100.0%			

Moisture %	3.8
------------	-----



The material tested complies with BS EN 12620 grading requirements

Signed



Dated

4th June 2026

