			Cons	rt Cole sultants egsoils consultan	СУ			
		8 Lincoln Court Los	London Road, Liphook, Hampshire GU30 7TB					
	Tel: 0330 043 0523 Email: albert@albertcoleconsultants.co.uk  AGGREGATE GRADING ANALYSIS							
	Client Smalldene Midlands							
	Sample Ref.	Omandene Wildian	24.4	136				
	Source		Armoury Road, Small Heath					
	Material Description  Date of Sample  Date of Test  Sample Weight		10-20mm  3rd December 2024  12th December 2024  1000					
	Campic Weigi		10	00				
	Sieve Size	Cum. Weight	% Weight	% Passing By Weight	Limits %	Pass/ Fail		
	40.0mm	0.00	0.0%	100.0%	100	PASS		
	31.5mm	12.00	1.2%	98.8%	98-100	PASS		
	20.0mm	98.00	9.8%	90.2%	85-99	PASS		
	10.0mm	906.00	90.6%	9.4%	0-20	PASS		
	4.0mm	981.00	98.1%	1.9%	0-5	PASS		
	PAN	1000.00	100.0%					
			Moisture %	3.8				
	Grading Curve							
100.0%				$\neg$				
							_	
							_	
75.0%								
50.0%								
					\			
25.0%				/				
0.00/								
0.0%	40.0mm	31.5mi	m 20	0.0mm	10.0mm	4.0mm		
		ested complies with	BS EN 12620 gra		S			
				Dated	12th Decembe	r 2024		
	Signed	_	S -					
	Signed							
	Signed							