




AGGREGATE GRADING ANALYSIS

Client: Smalldene Midlands Ltd

Sample Ref.	26.135
Source	Armoury Road, Small Heath
Material Description	20-40mm
Date Sample Received	26th May 2026
Date of Test	3rd June 2026
Sample Weight (g)	2000

Sieve Size	Cum. Weight Retained	% Weight Retained	% Passing By Weight	Limits %	Pass/Fail
80mm	0.00	0.0%	100.0%	100	PASS
63mm	0.00	0.0%	100.0%	98-100	PASS
40mm	243.00	12.2%	87.8%	80-99	PASS
20mm	1695.00	84.8%	15.2%	0-20	PASS
10mm	1945.00	97.3%	2.7%	0-5	PASS
Pan	2000.00	100.0%			

Moisture % 4.70%



Signed

Dated

4th June 2026

on behalf of Albert Cole Consultants

