


AGGREGATE GRADING ANALYSIS

Client: Smalldene Midlands

Sample Ref.	24.433
Source	Armoury Road, Small Heath
Material Description	6F5
Date Sample Received	3rd December 2024
Date of Test	12th December 2024
Sample Weight (g)	3000

Sieve Size	Cum. Weight Retained	% Weight Retained	% Passing By Weight	Limits %	Pass/Fail
125mm	0.00	0.0%	100.0%	100	PASS
80mm	68.00	2.3%	97.7%	75-99	PASS
40mm	493.00	16.4%	83.6%	50-90	PASS
20mm	1783.00	59.4%	40.6%	30-75	PASS
10mm	2108.00	70.3%	29.7%	15-60	PASS
2mm	2545.00	84.8%	15.2%	0-35	PASS
0.063mm	2867.00	95.6%	4.4%	0-12	PASS

Moisture %	5.70%
------------	-------



Signed



Dated

12th December 2024

on behalf of Albert Cole Consultants