




AGGREGATE GRADING ANALYSIS

Client: Smalldene Midlands Ltd

Sample Ref.	24.439
Source	Armoury Road, Small Heath
Material Description	0-6mm
Date of Sample	3rd December 2024
Date of Test	12th December 2024
Sample Weight	750

Sieve Size	Weight Retained	% Weight Retained	% Passing By Weight	Limits %	Pass/Fail
8.0mm	0.00	0.0%	100.0%	N/A	NA
6.0mm	0.00	0.0%	100.0%	N/A	N/A
4.0mm	52.00	6.9%	93.1%	N/A	N/A
2.0mm	120.00	16.0%	84.0%	N/A	N/A
1.0mm	189.00	25.2%	74.8%	N/A	N/A
500um	241.00	32.1%	67.9%	N/A	N/A
250um	450.00	60.0%	58.4%	N/A	N/A
63um	733.00	97.7%	2.3%	N/A	N/A
PAN	6.00	0.8%		N/A	N/A

Moisture %	7.90%
------------	-------



Signed

Dated

12th December 2024