



NC PROOFBOARD®

Hi-Temp Density 48 (HT-D48) Datasheet

2036 Nevada City Hwy
Box 573

Grass Valley, CA 95945

Ph: (530) 272-1133

Fax: (530) 272-1070

Email: sales@goldenwestmfg.com

Web: www.goldenwestmfg.com

DESCRIPTION & APPLICATION:

HT-D48 is a rigid, High Density Urethane, (HDU), Tooling/Modeling board designed for Prototype Machining, Water Jet Cutting, Pattern Making, Thermoforming, Prepreg Composite Layout Tooling Vacuum Form Tooling, Tool Path Proofing, Lost Wax Casting Masters, Master Model Making, Artistic Carving Blocks, Indoor and Outdoor Signage. NC Proofboard is made in the USA.

HT-D48 is formulated with eco-friendly, "Green" urethane components. The new NC Proofboard material has a Certified "Carbon Foot Print" of 3 to 1 and a Certified "Rapidly Renewable Green Resource Content" of 11.9%. This means each 3"x 4"x8' sheet of D-20 saves 19 pounds of plastic material which assists meeting LEED requirements for obtaining USGBC and ICC 700 building credits.

NC Proofboard **does not contain: CFCs or VOCs.** See MSDS for details.

NC Proofboard comes in standard sizes of 20"x60", 24"x60", 30"x80", 48"x60" 4'x8', 4'x10', 5'x8' and 5'x10'. Thickness ranges from 1/2" to 24". Custom bonded blocks available in any size. NC Proofboard standard densities are 15, 18, 20, 30, 34, 40, 48, 60, 70, & 75 pcf. Other densities available.

NC Proofboard is **non-abrasive**, can be machined with HSS bits or cut with any standard cutting tool. NC Proofboard's tight cell structure allows adjusting spindle speed & table feed to produce either chips or dust as desired. NC Proofboard does not outgas or affect prepreg resin cure.

NC Proofboard can be bonded to itself or most other substrates using one part urethane or, a two part, epoxy adhesive available from Goldenwest Manufacturing, Inc.

PHYSICAL PROPERTIES:

Density	ASTM D-1623	48 lbs./Cubic Foot
Compressive Strength	ASTM D-1621	3,049 psi
Compressive Modulus	ASTM D-1621	101,228 psi
Tensile Strength	ASTM D-1623	1,936 psi
Tensile Modulus	ASTM D-1623	156,548 psi
Shear Strength	ASTM C-273	2,175
Shear Modulus	ASTM C-273	67,840 psi
Flexural Strength Method 1A	ASTM D-790	2,648 psi
Flexural Modulus Method 1 A	ASTM D-790	108,201 psi
Hardness - Shore D	ASTM D-2240	92
Elongation		5.3%
Dimensional Stability	ASTM D-2126	1.2% Max.
Water Absorption	ASTM D-2842	0.03% by Vol. after 96 hrs.
Closed Cell Content	ASTM D-2856	97%
"K" Value Insulation Factor	ASTM C-177	1.20
Impact Resistance	0° 4.6 oz. 1" Dia. 9'6" drop	No cracking observed
Freeze Thaw	ASTM D-2126, 25 Cycles	No de-bonding or distortion occurred
Mold and Mildew Resistance	ASTM D-3273	Does not support growth
Dielectric Constant	ASTM D-1678	1.3
Maximum Service Temperature	Dry	300° F
Coefficient of Thermal Expansion (CTE)		26 X 10 ⁻⁶ °F
Glass Transition	DMA/TMA	284°F
Specific Heat	ASTM E-1269	0.235
Flammability Tests:	FAR 25.853 Vertical Burn	Pass
	MIL P 26514 Burn Test	Pass
	ASTM D-1692-74 Burn Test	Pass
	ASTM D635-06 Burn Test	Pass

Follow heat temperature ramping of 1°F up per minute & 2°F down per minute.

Questions? Please contact Goldenwest Manufacturing, Inc.

(530) 272-1133 or email sales@goldenwestmfg.com

www.goldenwestmfg.com

WARRANTY: All recommendations for product use have been derived from experience and test data believed to be reliable. We warrant and guarantee the uniformity of our products within manufacturing tolerance. However, since the use of our products is beyond our direct control, they are furnished upon the condition that each party shall make his/her own tests to determine their suitability for his/her particular purpose. Except as stated herein, Goldenwest Manufacturing Inc. makes no warranty or guarantee, expressed or implied, and disclaims all responsibility for results obtained, nor assumes any liability for any damages, whether arising out of negligence or breach of guarantee and is hereby expressly limited to replacement of product only. For additional information on product handling, please refer to NC Proofboard MSDS.