

## Horizontal Road & Deck Patching Mortar Kit

### DESCRIPTION:

**RepCrete QP** is a unique three-component rapid curing, non-shrink, hybridized polymer based elastomeric concrete that cures to a dense, semi-flexible, weather, abrasion and impact resistant polymer mortar for the repair of spalls on roadways, bridges and parking decks. The combined **RepCrete QP A & B** polymers when mixed with its part C, (Polymer Treated Blended Aggregate) forms a mortar with excellent long-term installation properties for all types of repairs, or deep patches.

### FEATURES:

- New as well as old concrete surfaces
- Outstanding anti-spalling properties
- High-load bearing capacity
- Resists the effects of freeze-thaw cycling
- Excellent water repellency
- Chemical & Impact Resistant
- Fast drying in any temperatures
- New as well as old concrete surfaces

### USES:

- Pavements & Marine Platforms
- Airfield & Highway Pavement Repairs
- Concrete & Masonry Surfaces
- Parking Structures
- Bridges & Ramps

### TECHNICAL DATA:

Exceeds ASTM C881 Type III (Mortar)  
Meets: TxDot DMS- 6170 Type I Polymer Concrete

### COVERAGE GUIDE:

.6 Cu. Ft. – in a 6 Gallon Pail Kit

### PREPARATION:

All surface contamination must be removed by mechanical means, creating a surface profile of exposed sound aggregate that will provide a strong bond surface for the **RepCrete QP**. It is recommended to profile surface according to ICRI Guide 03732 to a minimum of CSP 3 by abrasive blasting. Apply **Rust Rehab** permanent rust converter to any exposed steel. Precondition the **RepCrete QP** to 72 degrees for 24 hours for best results. **RepCrete QP** may be heated up to 100°F to speed cure at colder temperatures. It is recommended to condition all components when the temperature is below 50°F.

### MIXING:

**RepCrete QP** is shipped in pre-measured .6 Cu. Ft. units. Mix these products **ONLY** in complete units. **DO NOT THIN** or add any solvents or other aggregates prior to mixing. Mix the .6 Cu. Ft. kit per instructions and in the prescribed order on the pail and TDS.

### PLACEMENT:

The blended batch must be applied to the surface in 5-10 minutes. Once spread out, working time will be approximately 1/2 hour depending upon temperature. It is extremely important that the material be thoroughly compacted. Care should be taken to assure good compaction on the vertical face of the joint and along the side of the block out or form. Just smoothing the top with a steel float *is not* compacting the mortar. A small margin trowel, wood block, or other means, can be used for compaction.

### CURING/DRYING TIME:

At 75°F. (Substrate & air temperature), the mortar will cure sufficiently to accept traffic in two hours. Higher temperatures will shorten the cure while lower temperatures will lengthen the cure time. For temperatures in excess of 100°F, or lower than 60°F, contact TuffTex for recommended procedures and cure time.

### CLEAN UP:

All tools, other application or mixing equipment must be cleaned at frequent intervals and while **RepCrete QP** remains soft and uncured. Clean with **TuffTex Solvent 100**, or local approved solvent.

### PACKAGING:

6 Gallon Kit (.6 Cu.Ft.): is made up of equal volumes of “A” and “B” polymers, 30 pounds of body aggregates, 20 pounds of 3/8” pea gravel, and a 6 pound bag of topping sand. **(All aggregates are pre-treated)**. The entire contents come in a 6 gallon pail in which the material can mixed with the **RepCrete Quick Pail Mixer** or a 1/2 hp heavy-duty drill with the **RepCrete Mixer Stand**.

Bulk Mortar and Overlay Kits are also available in 10, 30, 100, & 250 Gallon vessels. Treated Sands & Aggregates are available in 50 lb. sacks, 2500 lb. bins, and 2500 lb. Super Sacks.

**PHYSICAL PROPERTIES:**

Gel Time (Tex-614-J) . . . . .	9 minutes
Compressive Strength (ASTM C-579, B)	
24 Hours. . . . .	1710 psi
7 Days. . . . .	1820 psi
28 Days. . . . .	2140 psi
Wet Bond Strength (Tex-618-J)	
7 Days. . . . .	110 psi
Compressive Stress at 0.1 in (Tex-618-J)	
7 Days . . . . .	733 psi
Resilience, % (Tex-618-J)	
7 Days . . . . .	97.2%
Thermal Compatibility (ASTM C884)	
7 Days . . . . .	Pass
Flexural Strength	
24 Hours. . . . .	740 psi
28 Days. . . . .	1008 psi
Bond Strength	
24 Hours. . . . .	203 psi
28 Days. . . . .	355 psi
Modulus	
24 Hours. . . . .	12270 psi
28 Days. . . . .	23641 psi
Specific Gravity. . . . .	1.84
Absorption . . . . .	0.33%

**CHEMICAL RESISTANCE:**

ASTM D 471, . . . . .	25°C (77°F) after 22 hr.
Chemical Effects	
Deicers	None
Motor Oil	None
Sodium Chloride Solution (5%)	None
<u>Hydraulic Brake Fluid</u>	<u>None</u>

**COLOR:**

Gray or Black

**STORAGE:**

The material should be stored between 40°-90°F (5°-33°C) in a cool, dry area away from direct sunlight. For best results, condition material to 65°- 85°F before using.

**SHELF LIFE:**

Shelf life of properly stored, unopened containers is 24 months.

**EFFECT OF TEMPERATURE ON SET TIME:**

TEMPERATURE	SET TIME	RETURN TO SERVICE
80-100° F.	5-6 minutes	20 minutes
60-80° F.	10 minutes	30 minutes
40-60° F.	20 minutes	60 minutes
20-40° F.	30 minutes	90 minutes

**CAUTION:**

**READ SDS PRIOR TO USING PRODUCT**  
 Use with adequate ventilation. Wear protective clothing, gloves and eye protection. (Goggles, Safety Glasses and/or Face Shield) Keep out of the reach of children. Do not take internally. In case of ingestion, seek medical help immediately. May cause skin irritation upon contact, especially if prolonged or repeated exposure. If skin contact occurs, wash immediately with soap and water and seek medical help as needed. If eye contact occurs, flush immediately with clean water and seek medical help as needed. Dispose of waste material in accordance with federal, state and local requirements. Cured resins are Innocuous. Dispose of waste material in accordance with federal, state and local requirements.

**WARRANTY:**

Due to the use of this product beyond our control, we assume no liability for damages of any kind, and the user accepts the product "as is" and without warranties, expressed or implied, from either **TuffTex Materials** or its agents. The suitability of the product for an intended use shall be solely up to the user. Our only obligation shall be to replace or pay for any material proved defective, with our liability limited to the purchase price of materials supplied by us.

**DISCLAIMER:**

Refer to the MSDS sheet before use. The information and recommendations set forth in this Product Data Sheet are based upon tests conducted by or on behalf of TuffTex Materials. Such information and recommendations set forth herein are subject to change and pertain to the product offered at the time of publication. Published technical data and instructions are subject to change without notice. Contact your local Nova-Tuff distributor or technical representative for additional technical data and instructions.

**OSHA Status:** This Material Safety Data Sheet (MSDS) has been prepared in compliance with the federal OSHA Hazard Communication Standard 29 CFR 1910.1200. This product is not considered to be a hazardous chemical under that standard.