

Bright Compacted 19x19


Rotation Resistant

Right Regular Lay
 EEIPS (Extra Extra Improved Plowed Steel) Grade
 Independent Wire Rope Core (IWRC)
 Compacted With C-Lube

Maximum Breaking Strength 87.9 Tons

Diameter	Construction	Weight / Foot - Lbs	Breaking Strength - Tons
1/2	19x19(S)	0.54	14.6
9/16	19x19(S)	0.69	18.5
5/8	19x19(S)	0.85	22.7
3/4	19x19(S)	1.25	32.4
7/8	19x19(S)	1.68	43.8
1	19x19(S)	2.17	56.9
1-1/8	19x19(S)	2.75	71.9
1-1/4	19x19(S)	3.45	87.9





Compacted 35x7 Wire Rope


Rotation Resistant

Right Regular lay
2160 Grade Compacted & Rotation Resistant

Maximum Break Strength 1,232 KN (KiloNewton)

Rope Diameter (MM)	Weight In Foot In Lbs	Break Strength (Tons)
13	0.54	162
16	0.8	251
18	1.01	308
19	1.14	344
20	1.29	382
22	1.56	466
23	1.85	555
25.4	2.1	628
26	2.16	660
28	2.55	758
32	3.31	980
34	3.73	1134
36	4.19	1232





Bright 8x25 IWRC

Rotation Resistant


Right Regular Lay

E. I.P.S Grade Wire Rope

High Quality Cable with Maximum Break Strengths

Rope Diameter	Weight In Foot In Lbs	Break Strength (Tons)
3/8	0.26	6.63
1/2	0.47	11.60
9/16	0.60	14.70
5/8	0.73	18.10
3/4	1.06	25.90





Bright 19x7 IWRC

Rotation Resistant

Right Regular Lay


E. I.P.S Grade Wire Rope

High Quality Cable with Maximum Break Strengths

Rope Diameter	Weight In Foot In Lbs	Break Strength (Tons)
1/4	0.11	2.77
5/16	0.18	4.30
3/8	0.25	6.15
7/16	0.35	8.33
1/2	0.45	10.80
9/16	0.58	13.60
5/8	0.71	16.80
3/4	1.02	24.00
7/8	1.39	32.50
1	1.82	42.20
1-1/8	2.30	53.10
1-1/4	2.85	65.10




Bright Drill Line 6x19 & 6x26 IWRC



Right Regular Lay

E.I.P.S. Wire Grade

Rotary / Standard Drill Line With C-Lube
Maximum Strength Of 114 Tons




Diameter (Inches)	Construction	Weight / Ft. in Lbs	Breaking Strength in Tons
7/8	6x26(W/S)	1.42	39.8
1	6x26(W/S)	1.85	51.7
1 1/4	6x19(S)	2.89	79.9
1 3/8	6x19(S)	3.50	96
1 1/2	6x19(S)	4.16	114

Bright Drill Line 6x21 - Fiber Core


Right Regular Lay

E.I.P.S. Wire Grade

Rotary / Standard Drill Line With C-Lube
Maximum Strength Of 114 Tons



Diameter (Inches)	Construction	Weight / Ft. in Lbs	Breaking Strength in Tons
7/8	6x26(W/S)	1.42	39.8
1	6x26(W/S)	1.85	51.7
1 1/4	6x19(S)	2.89	79.9
1 3/8	6x19(S)	3.50	96
1 1/2	6x19(S)	4.16	114



Drawn Galvanized 19x7 IWRC

Rotation Resistant

Right Regular Lay

E. I.P.S Grade Wire Rope


High Quality Cable with Maximum Break Strengths

Rope Diameter	Weight In Foot In Lbs	Break Strength (Tons)
1/4	0.11	2.77
5/16	0.18	4.30
3/8	0.25	6.15
7/16	0.35	8.33
1/2	0.45	10.80
9/16	0.58	13.60
5/8	0.71	16.80
3/4	1.02	24.00
7/8	1.39	32.50
1	1.82	42.20
1-1/8	2.30	53.10
1-1/4	2.85	65.10



Sand Line Wire Rope

Bright 6x7 Fiber Core (P.P.C)



Right Regular Lay

I.P.S. Wire Grade Sand Line With B-Lube


Maximum Strength Of 15.9 Tons

Diameter (Inches)	Construction	Weight / Ft. in Lbs	Breaking Strength in Tons
1/2	6x7	0.38	10.3
9/16	6x7	0.48	14.3
5/8	6x7	0.59	15.9




Galvanized Fiber Core Trawl Cable

6x7 & 6x19 IWRC



Right Regular Lay

I.P.S Grade Heavy D - Lube



Diameter (Inches)	Construction	Weight / Ft. in Lbs	Breaking Strength in Tons
5/16	6x7	0.15	3.69
3/8	6x7	0.21	5.27
7/16	6x7	0.29	7.14
1/2	6x7	0.38	9.27
9/16	6x7	0.48	11.70
5/8	6x7	0.66	14.30
5/8	6x19	0.66	14.30
3/4	6x19	0.95	21.40

