



Attractive, high performance, heavy duty homogeneous sheet and tile floorcovering with a polyurethane surface treatment which provides an excellent foundation for an easy, ongoing maintenance regime. Featuring a duotone marbleised decoration, XL PU is available in a broad palette of vibrant shades.

Demonstrating outstanding durability and abrasion resistance and available in a choice of gauges, XL PU is recommended for public, institutional and commercial buildings as well as hospitals, schools, laboratories and offices.

PE CODE: AL/CPI




PRODUCT SPECIFICATION



- The flooring shall be Polyflor XL PU, as manufactured by Polyflor Ltd. of Manchester, England.
- The flooring shall be flexible PVC sheet flooring in 2.0mm.
- · It shall be homogeneous and monolayer in construction.
- The flooring material shall conform fully with the requirements of EN 649/EN ISO 10581.
- In acccordance with EN 649, the in-use classification must be at least 23/34/43, as defined in EN 685/EN ISO 10874, i.e. domestic areas with intense use; commercial areas with very heavy use; and light industrial areas with heavy use for the 2.0mm gauge.
- In respect of flamespread, the flooring shall have been fully tested to EN 13501-1 and certified as having Class BfI-S1.
- The flooring shall have been fully tested to ASTM E648 and certified as having passed with a Class 1 rating, making it suitable in institutional, commercial and public buildings.



- The product must have been fully tested for abrasion resistance to the Frick Taber test EN 660-2 and be in abrasion group M, as defined in EN 649.
- With regard to EN 13893 for slip resistance, the flooring shall be classified DS, making it suitable for use in areas which are predominantly dry, but with occasional spillage.
- With regards to EN ISO 10581 the product shall be classified Type II.
- This product does not accumulate static charges above 2kV and is classified as 'antistatic' when tested to EN 1815. For specialist applications where there is a requirement to dissipate the electrostatic charge, see the Polyflor ESD product ranges.
- · The flooring must be available in 2.0 metre width, to minimise the number of joints.
- In respect of light fastness, the flooring shall have been fully tested to ISO 105-B02 Method 3 and obtain ≥6





- Generic EN 15804 Environmental Product Declaration (EPD) available on request.
- The manufacturer should provide a facility to take back and recycle waste vinyl flooring material through the Recofloor scheme.
- The flooring shall be tested to and pass key independent, international standards for low VOC emissions.
- The product will achieve BES 6001 certification for responsible sourcing, obtaining a Excellent rating.



- The manufacturer of the floorcovering must be in possession of a valid quality systems certificate, showing compliance with BS EN ISO 9001.
- The manufacturer of the floorcovering must be in possession of a valid environmental certificate, showing compliance with ISO 14001.





- The adhesive used must be approved by Polyflor, to ensure full product compatibility.
- Products must be fully conditioned to the environment in which they are to be installed, as outlined by Polyflor.
- $\bullet\,$ Installation must be carried out in accordance with BS 8203 and the instructions of Polyflor.
- All joints must be welded to produce hygienic, continuous floors.
- Suitable for use with underfloor heating up to 27°C. See Polyflor Technical Information for details.



 Polyflor homogeneous PUR, heterogeneous PUR and Polysafe safety flooring ranges are compatible for use with the most commonly used alco-based hand gels. Some alco-based hand gels contain a high concentration of ethanol and to discuss their compatibility with XL PU, contact Polyflor Customer Technical Services. For information regarding handling and installation, adhesives, maintenance, applications, chemical resistance and product warranty, consult Catalina Products International (714) 716-1667.

· A moisture test must be carried out, to ensure that the subfloor has dried out to a level consistent with the application of vinyl flooring. The test should

• At the date of issue the data presented is correct. However, Polyflor Ltd. reserve the right to make changes which do not adversely affect performance or quality.































