

# CAMBRIA™

## TECHNICAL DATA SHEET



CATALINA  
PRODUCTS  
INTERNATIONAL

714.716.1667 | [contact@catalinaproducts.international](mailto:contact@catalinaproducts.international)

### DESCRIPTION

Cambria™ goes above and beyond by withstanding severe moisture and alkalinity. Offering the upfront benefits of a PSA, it quickly transitions; fully cross-linking into a hard-set to securely lock your flooring in place. With its aggressive, fast-grab design, Cambria™ handles the pressure of heavy rolling loads with ease.

### APPROVED FLOORING TYPES

HVT, LVP, LVT, rigid core [dryback], SVT, VCT, VET, woven  
Rubber (crumb, sheet, tile),  
Sheet (fiberglass, heterogeneous, homogeneous, woven)  
Stair Treads (rubber, vinyl)  
CARPET: Broadloom (6-ft vinylbacked)  
WOOD: Cork (cork-backed hard surface, underlayment)

### APPROVED SUBSTRATES & SURFACES

- APA underlayment grade plywood and OSB
- Association grade particleboard
- Cementitious and anhydrite screeds
- Cement backer board
- Concrete and radiant heated subfloors that do not exceed 85°F (30°C)
- Existing well-bonded non-cushion-backed vinyl, tile and sheet flooring
- Fully secured cork underlays
- Gypsum and lightweight concrete (primed with Universal Primer)
- Terrazzo (properly prepared with all waxes and surface finishes removed)

### SUBSTRATE TESTING

RH - 99% [ASTM F2170]  
pH - 5-12 [ASTM F710]  
MVER - 12 lbs [ASTM F1869]

### PERCAUTIONARY NOTE:

- This product does not form a moisture vapor barrier and will not protect flooring from moisture damage.

### SUBSTRATE & SURFACE PREPARATION

Follow flooring manufacturer's guidelines for allowable levels of moisture. Substrate must be prepared per ASTM F710 standards including, but not limited to the following:

- Concrete floors must be dry, clean, smooth and structurally sound. They shall be free of any foreign materials that might prevent adhesive bond, including dust, dirt, solvent, paint, wax, oil, grease, contaminants from sweeping compounds, residual adhesive, adhesive removers, incompatible sealers, fire-retardant chemicals, fungicides, release agents, alkaline salts, excessive carbonation, laitance, mold, mildew, and curing, sealing, hardening or parting compounds.
- Fill all surface cracks, grooves, depressions, control joints and non-moving joints with moisture resistant patching and self-leveling compounds, allow to fully cure and correct high spots before applying adhesive.

# CAMBRIATM

## TECHNICAL DATA SHEET



CATALINA  
PRODUCTS  
INTERNATIONAL

714.716.1667 | [contact@catalinaproducts.international](mailto:contact@catalinaproducts.international)

### SUBSTRATE & SURFACE PREPARATION CONTINUED

- The substrate, adhesive and flooring must be acclimated in an enclosed building with the HVAC operational at service temperature, between 60-95°F (15-35°C), and between 30-65% relative humidity, for at least 72 hours prior to, during, and permanently after installation.
- When installing over radiant heated subfloors, turn the heat off for 24 hours before, during and after installation. Failure to turn the heat off may result in shortened working time of the adhesive. When turning radiant heat back on, raise it incrementally, not to exceed a change of more than 5 degrees per hour to a maximum of 85°F (29°C).

### PRECAUTIONARY NOTES:

- Concrete must be placed in strict accordance with applicable standards and specifications. An intact moisture vapor retarder must be present below the concrete (see ASTM E1745), must be fully cured (at least 45 days), without hydrostatic pressure, without pressurized liquid from any source, and free of surface alkaline salt crystallization.
- Flooring must be acclimated per manufacturer's guidelines.

### APPLICATION INSTRUCTIONS

Follow flooring manufacturer's guidelines for layout, design and any special precautions for installation.

1. Spread adhesive using required tools.
2. Install flooring per instructions below dependent upon desired application (flash and working times dependent upon temperature and humidity).
  - Dry-set, PSA (porous and non-porous substrates)
    - Wait 30-60 minutes after adhesive is spread to allow flash off. Adhesive will darken to visually cue installer.
    - Working time ~3 hours.
  - Semi-wet set (porous substrates only)
    - Wait 20-30 minutes after adhesive is spread to allow it to skin over.
    - Working time 20-30 minutes.
  - For sheet vinyl, back-roll adhesive with adhesive saturated roller to smooth out trowel ridges.
3. Roll and cross roll floor with 75-100 lb roller at the end of the installation to ensure proper adhesive transfer.
  - Sheet goods - roll from center toward perimeter to expel trapped air.
  - Check flooring after 2 hours and roll again if necessary.

### PERCAUTIONARY NOTES:

- Although this is a high-moisture tolerant adhesive, it does not form a moisture vapor barrier and will not protect flooring from moisture damage.
- Wait 24 hours before heat welding sheet goods.
- Wait 72 hours before wet mopping, stripping/finishing the floor.
- Reseal lid when not in use to protect product.

# CAMBRIATM

## TECHNICAL DATA SHEET



CATALINA  
PRODUCTS  
INTERNATIONAL

714.716.1667 | [contact@catalinaproducts.international](mailto:contact@catalinaproducts.international)

### REQUIRED TOOLS AND COVERAGE

- Trowel dimensions are width X depth X spacing. Coverage is approximate and may vary depending on porosity of substrate and the angle at which the trowel is held.

Flooring Type	Tool* (images not to scale)	Estimated Coverage
Porous: HVT, LVT/LVP, Carpet tile (hard- and soft-backed), Sheet goods (vinyl, homogeneous, heterogeneous), Rubber (tile and sheet), WPC/WSC, Corkbacked hard surface, Cork underlayment, Stair treads (rubber and vinyl)	1/16" x 1/16" x 1/16" (1.6mm x 1.6mm x 1.6mm) Sq Notch	150-180 sf/gal
Non-porous: HVT, LVT/LVP, Carpet tile (Hard- and soft-backed), Sheet goods (vinyl, homogeneous, heterogeneous), VCT/VET, Stair treads (rubber and vinyl)	1/16" x 1/32" x 1/32" (1.6mm x .8mm x .8mm) U Notch	220-260 sf/gal
Hard-backed carpet tile, Fiberglass sheet goods	3/8" (10mm) Shortnap paint roller	Up to 350 sf/gal

\*It is the sole responsibility of the contractor/installer to determine the proper porosity of the subfloor, apply the correct amount of adhesive for the job conditions and ensure that all instructions, procedures, and practices are strictly adhered to.

### CLEANING INSTRUCTIONS

**While product is still wet:** Use a damp cloth and water to remove.

**While product is still soft:** Use denatured alcohol, mineral spirits, or an adhesive remover/stripper. Always check compatibility on a piece of scrap flooring.

### STORAGE

This product should be stored at temperatures between 50-90°F (15-32°C). While this product is freeze-thaw stable, it is necessary to protect it from freezing. Freeze/thaw stable to 10°F (-12°C).

### CAUTION

DO NOT take internally. If swallowed, DO NOT induce vomiting. Call a physician immediately. KEEP OUT OF REACH OF CHILDREN.

### WARRANTY INFORMATION

For warranty information, call CPI at 714-716-1667, visit us on the web at [www.catalinaproducts.international](http://www.catalinaproducts.international) or e-mail us at [contact@catalinaproducts.international](mailto:contact@catalinaproducts.international). Flooring manufacturer's written pre-installation and installation instructions must be strictly followed or the warranty will be void.

# CAMBRIATM

## TECHNICAL DATA SHEET



CATALINA  
PRODUCTS  
INTERNATIONAL

714.716.1667 | [contact@catalinaproducts.international](mailto:contact@catalinaproducts.international)

PRODUCT CHARACTERISTICS	
MOISTURE	Product Classification Hard-Set, Transitional Pressure Sensitive® Adhesive
	Base Chemistry Hybrid acrylic
	Curing Method Proprietary cross-linking
	Appearance/Color Light tan (wet), dark, translucent tan (dry)
	Consistency Smooth, medium viscosity liquid
	Application Easy troweling
	Flammability Non-flammable
	Freeze/Thaw Stable to 10°F (-12°C) [3 cycles]
	Shelf Life [Unopened Container at 70°F] 2 years
TIME	Moisture Control No
	RH [ASTM F2170] 99%
	pH 5-12
	MVER [ASTM F1869] 12 lbs
TRAFFIC	Open Time 20-30 min (semi-wet-set)
	Flash Time 30-60 min (PSA)
	Working Time 20-30 min (Semi-wet-set); 3 hrs (PSA)
	Cure Time 12 hrs
	Pot Life N/A
SUSTAINABILITY	Light Traffic 0 min (PSA), 12 hrs (Semi-wet-set)
	Heavy Traffic 24 hrs
	Rolling Loads 48 hrs
ACOUSTICS	Solvents No
	Isocyanates No
	VOC Wet Applied [g/L] [SCAQMD Rule #1168] < 21 g/L
	LEED v4/4.1 Points Contributes to low emitting materials
	Certifications FloorScore®, Green Label Plus®, GREENGUARD®, Material Health Certificate - Silver
	IIC No
	STC No

### RECOMMENDED SUBSTRATES

Cambria pressure sensitive adhesive is a quick tack glue specifically designed for the installation of vinyl, heterogeneous, and homogeneous flooring materials. Cambria is recommended for the following substrate composite:

- Suspended wood substrates
- Wood substrates
- Concrete
- Light weight concrete
- Gypsum