



Date Sampled:

Date Tested: 6-15-17

Plant:

Source:

Aggregate: Mound Mix

Commodity Code:

Sieve Size	Weight Retained	Percent Retained	Percent Passing	Product Specifications	Notes
#5	8	2	98		
#10	41	8	92		
#18	87	17	83		
#35	127	25	75		
#60	173	35	65		
#100	207	41	59		
#270	258	52	48		
Total	500				

		F.M.:	
S.E.	0.9 / 10.0	9	9
	0.9 / 10.0	9	9
C.V.		in.	
Durability	/		
		in.	
L.A.R.T.	100 Rev.		
	500 Rev.		

Sampled By:

Tested By: A. B



Date Sampled:

Date Tested: 6.7.17

Plant:

Source:

Aggregate:

ANGEL MIX

Commodity Code:

Sieve Size	Weight Retained	Percent Retained	Percent Passing	Product Specifications	Notes
#5	0	0	100		
#10	21	6	94		
#18	104	23	77		
#35	182	40	60		
#60	248	55	45		
#100	288	64	36		
#270	334	74	26		
Total	453				

S.E.

F.M.:

Sampled By:

C.V.

2.2/10.2 22
2.4/10.3 23 > 23

Tested By: KP

Durability

1

in.

L.A.R.T.

100 Rev.

500 Rev.



Date Sampled:

Date Tested: 6-15-17

Plant:

Source:

Aggregate:

TRAK Mix

Commodity Code:

Sieve Size	Weight Retained	Percent Retained	Percent Passing	Product Specifications	Notes
# 5	0	0	100		
#10	26	5	95		
#18	116	23	77		
#35	208	42	58		
#60	283	57	43		
#100	320	64	36		
#270	381	76	24		
Total	500				

F.M.:

Sampled By:

S.E.

2.5 / 12.7 20
2.3 / 12.7 18 > 19

C.V.

in.

Tested By:

A.B

Durability

/

in.

L.A.R.T.

100 Rev.

500 Rev.