

1200x1800mm
120x180cm



**fantastic
format**



1200 x 1800 mm

CRYSTAL ROSE



12000 x 18000

RANDOM



1200 x 1800 mm

FITZ GREY



12000 x 18000

RANDOM



1200 x 1800 mm

GRISIAL GREY




12000 x 18000

RANDOM



1200 x 1800 mm

GRISIAL PINK



12000 x 18000

RANDOM



1200 x 1800 mm

MELTONE BIANCO




12000 x 18000

RANDOM



1200 x 1800 mm

OMANI BIANCO



12000 x 18000

RANDOM



1200 x 1800 mm

PATAGONIA IDEAL




12000 x 18000

RANDOM



1200 x 1800 mm

ARMANI COOPER




12000 x 18000

RANDOM




1200 x 1800 mm

CELLOSIA BLUE



12000 x 18000

RANDOM




1200 x 1800 mm

ALMOND GREEN




12000 x 18000

RANDOM





1200 x 1800 mm

AMAZONITE AQUA



12000 x 18000

RANDOM



1200 x 1800 mm

PATAGONIA SADDLE



12000 x 18000

RANDOM



TECHNICAL SPECIFICATIONS

| CHARACTERISTICS | STANDARD AS PER ISO-13006/EN14411 GROUP B1A | MEAN VALUE OF PGVT | MEAN VALUE OF GVT | TEST METHOD |
|--|---|---------------------------|---------------------------|--------------|
| REGULATORY PROPERTIES | | | | |
| Deviation in length & width | ±0.5 % | ±0.1 % | ±0.1 % | ISO-10545-2 |
| Deviation in thickness | ±5.0 % | ±4.0 % | ±4.0 % | ISO-10545-2 |
| Straightness in side | ±0.5 % | ±0.1 % | ±0.1 % | ISO-10545-2 |
| Rectangularity | ±0.6 % | ±0.1 % | ±0.1 % | ISO-10545-2 |
| Surface flatness | ±0.5 % | ±0.2 % | ±0.2 % | ISO-10545-2 |
| Color difference | Unaltered | No change | No change | ISO-10545-16 |
| Glossiness | As per mfg. | Min. 90 | Min.10 | GLOSSOMETER |
| SURFACE MECHANICAL PROPERTIES | | | | |
| Water absorption | < 0.50 % | < 0.20 % | < 0.20 % | ISO-10545-3 |
| Apparent density | > 2.0 g/cc | > 2.10 g/cc | > 2.10 g/cc | DIN 51082 |
| MASSIVE MECHANICAL PROPERTIES | | | | |
| Modulus of rupture | Min. 35 N/mm ² | Min. 40 N/mm ² | Min. 40 N/mm ² | ISO-10545-4 |
| Breaking strength | Min. 1300 N | Min. 2000 N | Min. 2000 N | ISO-10545-4 |
| Impact resistance | As per mfg. | Min. 0.55 | Min. 0.55 | ISO-10545-5 |
| SURFACE MECHANICAL PROPERTIES | | | | |
| Surface abrasion resistance | As per mfg | Min. Class-3 | Min. Class-4 | ISO-10545-7 |
| MOH's hardness | As per mfg | Min. 4 | Min. 5 | EN 101 |
| THERMO HYDROMETRIC PROPERTIES | | | | |
| Frost resistance | No damage | No damage | No damage | ISO-10545-12 |
| Thermal shock resistance | No damage | No damage | No damage | ISO-10545-9 |
| Moisture expansion | Nil | Nil | Nil | ISO-10545-10 |
| Thermal expansion (COE) | Max. 9.0x10 ⁻⁶ | Max. 6.5x10 ⁻⁶ | Max. 6.5x10 ⁻⁶ | ISO-10545-8 |
| Crazing resistance | As per mfg. | Min. 10 Cycle | Min. 10 Cycle | ISO-10545-11 |
| CHEMICAL PROPERTIES | | | | |
| Chemical resistance | No damage | No damage | No damage | ISO-10545-13 |
| Stain resistance | Resistant | Resistant | Resistant | ISO-10545-14 |
| SAFETY PROPERTIES | | | | |
| Slip resistance | As per mfg. | > 0.40 | > 0.40 | ISO-10545-17 |
| Fire resistance | As per mfg. | Fireproof | Fireproof | N. A. |
| Lead & Cadmium given off by glazed tiles | As per mfg. | Doesn't yield Pb & Cd | Doesn't yield Pb & Cd | ISO-10545-15 |

PACKING DETAILS

| Size | Thickness (approx ^o) | Pieces / Box | Area / Box (approx ^o) | | Weight / Box (approx ^o) |
|-------------|----------------------------------|--------------|-----------------------------------|-------------|-------------------------------------|
| 1200x1800mm | 9mm | 2 pcs. | 4.32 sq.mtr. | 46.5 sq.ft. | 90 sq.ft. |