



Product Overview

Cu Rep 28

Acid Etch Replenisher

Product Description

Cu Rep 28 is a concentrated sodium chlorate based oxidizer for use with cupric chloride etching processes. Our ready-to-use, liquid formulation provides the safest, most stable oxidizer to handle. Proprietary rate enhancers afford substantially increased etch rates over generic sodium chlorate, hydrogen peroxide and chlorine gas.

Features

- ⊙ High oxidizer normality
- ⊙ Rate enhancing additives
- ⊙ Ready-to-use, liquid formulation

Benefits

- ⊙ Increases copper concentration and improves control
- ⊙ Increases etch rate without increasing acid normality
- ⊙ Safer, more stable and easier to handle than gaseous or solid oxidizers

Operating Parameters

Copper loading:	20 – 30 oz/gal (150 – 225 g/L)
Free acid normality:	0.5 – 3.0 N
ORP mV:	450 – 650 mV
Temperature:	120 °F – 140 °F

Storage

Store in original containers above 40 °F.

Safety

CAUTION! Cu Rep 28 is a strong oxidizer. Do not allow to contact strong acids or combustible materials. Avoid contact with eyes, skin and clothing. Wear chemical handler's gloves, goggles and protective clothing when handling. Do not allow to dry on clothing. Remove and wash contaminated clothing immediately. Read and understand Material Safety Data Sheet before using this product.

Notice

The information and recommendations, contained herein, regarding this product are, to the best of our knowledge, true and accurate. We make no guarantee of results because the conditions of actual use are beyond our control. We assume no liability for damages or penalties resulting from the use of this product or following our recommendations. Our recommendations and suggestions for use of this product are not intended to grant license to operate under or infringe any patent.