


W COAT



SPECIFICATION:

Wavelength (nm)	Reflection (average)	Reflection (absolute)
532nm	-	< 0.25%R
1064nm	-	< 0.25%R

Environmental (MIL – C – 675)

Adhesion	Fast Pull (Snap) LT-90 self-adhesive tape
Abrasion (moderate)	50 rubs (25 cycles) Cheesecloth @ 1lb
Abrasion (Severe)	40 rubs (20 cycles) Rubber Pad @ 2.5lb
Humidity	24 hours @ 95% RH (50 deg C)
Temperature Cycle	-60 deg C to +70 deg C