2800 SERIES CLEAR 2K WATER-BASED POLY TOPCOATS

CENTURION WOOD COATINGS



This is the benchmark for water-based, 2K, clear, polyurethane topcoats!

The technology behind our premium, self-sealing, clear 2800 Series 2K Water-Based Topcoats delivers excellent chemical and moisture resistance with outstanding non-yellowing properties and resistance to UV degradation. Fully cured, these coatings provide superior resistance to abrasion and black heel marks. They're designed for a variety of high-end cabinetry, architectural millwork, furniture and more and are primarily made with "green," bio-sustainable materials.

Clear Topcoats in the Centurion™ Wood Coatings 2800 Series

CW-3025	Clear Polyurethane Topcoat (flat)
CW-3026	Clear Polyurethane Topcoat (satin)
CW-3027	Clear Polyurethane Topcoat (semi-gloss)
CW-3028	Clear Polyurethane Topcoat (gloss)

- Outstanding non-yellowing transparency
- Can be used for refinished or new wood projects
- Superb chemical and moisture durability
- Excellent adhesion properties
- Tintable
- Meets or exceeds KCMA performance specs

EUROPEAN QUALITY MADE IN AMERICA



info@centurionwoodcoatings.com | Toll-free 877-258-8797
centurionwoodcoatings.com
2935 Almeta Lane, McKinney, TX 75069

EXPERT APPLICATION SYSTEMS



For a self-sealing system using new wood or refinishing

Make sure all surfaces are clean and sanded with 300 to 400 grit between coats.

1. Apply the 2800 Series Clear 2k Polyurethane Topcoat with 15% CW-4002 catalyst-hardener at 3-5 wet mils.
2. Catalyze the 2800 Series Topcoat with 15% CW-4002 catalyst-hardener. Apply 1-2 coats at 3-5 wet mils.

Hybrid water-based/solvent-based finishing system for new wood or refinishing

Make sure all surfaces are clean and sanded with 300 grit to 400 grit between coats.

1. Apply 1-2 coats of CS-2006 Clear Vinyl Sealer at 3-4 wet mils.
2. Catalyze the 2800 Series 2k Topcoat with 15% CW-4002 catalyst-hardener. Apply a minimum of 2 coats at 3-5 wet mils.





APPLICATION TIPS

General Spray Equipment Recommendations:
- Airless 310-308 1,200-1600 fluid pounds
- Turbine 4 stage minimum 1.3-1.8
- Air-assist 600-1200 fluid pounds .13-.09
- Hardener mix ratio is figured by weight

Always follow Technical Data Sheet of each product.
Pot life for 2800 series with CW-4002 Catalyst-Hardener at 15% is 4 hours.
Be sure to slowly pour catalyst into product while product is under agitation.

Scan this code to see more expert applications for Centurion™ Wood Coatings 2800 Series 2K Water-Based Polyurethane Topcoats

CENTURION
WOOD COATINGS

CIC COATINGS

info@centurionwoodcoatings.com
centurionwoodcoatings.com
Toll-free 877-258-8797
2935 Almeta Lane, McKinney, TX 75069

Follow Us