

## **FIX-O-FLEX BOOSTERPASTE**

**Properties:**

*FIX-O-FLEX BOOSTERPASTE* is a solvent-free and unplasticized accelerator for the *FIX-O-FLEX* adhesive and sealing compounds.

Depending on temperature and weather the tack-free times of different *FIX-O-FLEX* adhesive and sealing compounds can be significantly more reduced by mixing with small quantities of *FIX-O-FLEX BOOSTERPASTE*.

The use of *FIX-O-FLEX BOOSTERPASTE* is especially recommended for processing of *FIX-O-FLEX* products in areas with low or without air humidity.

**Technical data:****Substance data:**

|                        |                               |                     |
|------------------------|-------------------------------|---------------------|
| Consistency            | zähflüssig                    |                     |
| Colour                 | weiß                          |                     |
| Odour                  | geruchlos                     |                     |
| Spec. density (23°C)   | approx. 1.1 g/cm <sup>3</sup> | DIN EN ISO 2811-1   |
| Dyn. viscosity (23°C)  | approx. 6000 mPas             | DIN EN ISO 2555     |
| Processing temperature | 10 - 25°C                     | product temperature |
| Consumption            | max. 2.0 % *                  |                     |

(\* with reference to total mass of *FIX-O-FLEX* adhesive and sealing compound)

**Processing:**

The required quantity of *FIX-O-FLEX BOOSTERPASTE* is directly filled into the *FIX-O-FLEX* drum and stirred homogenously (free of streaks) by means of a slow-speed stirrer (e.g. drilling machine with stirring attachment).

Detailed information on dosage of *FIX-O-FLEX BOOSTERPASTE* can be found in the special Technical Data Sheets of *FIX-O-FLEX* adhesive and sealing compounds.

**Safety information:**

*FIX-O-FLEX BOOSTERPASTE* is not classified as hazardous according to Regulation (EC) 1272/2008 (CLP).

Even in the case of not classified products, the standard precautionary measures applicable for chemical products should be observed.

It is therefore necessary, before beginning processing, to become familiar with the precautions and safety advice as indicated in the material safety data sheet.

**Packaging:**

400 g plastic can

Bigger packaging on request.

**Storage:**

Shelf life at least 12 month in original packaging when stored in dry conditions between 15-25°C, protected from heat, frost and direct sunlight.



After the expiration the use of the product is generally not recommended, unless an approval has been provided by TPH. This approval can only be obtained by the quality assurance department of TPH releasing the material after verification of main properties being within specification.

**Disposal:**

Small quantities of cured product residues can be disposed of as normal domestic waste. Dispose of not cured product components must be effected in accordance with the corresponding local regulations. For further information please refer to the material safety data sheets.

**Legal notice:**

The correct and thus successful application of our products is not subject to our control. A guarantee can be issued for the quality of our products within the framework of our sales and supply conditions, however not for successful processing. All data and specifications in this specification sheet are based on the present state of the art and the right to changes and adaptations for the sake of development remains explicitly reserved. The consumption specifications designated by us can be only average empirical values, where deviations are possible on an individual basis and therefore cannot be excluded by us.

**TPH Bausysteme GmbH**  
Nordportbogen 8  
**D-22848 Norderstedt**

Tel.: +49 (0)40 / 52 90 66 78-0  
Fax: +49 (0)40 / 52 90 66 78-78  
e-mail [info@tph-bausysteme.com](mailto:info@tph-bausysteme.com)  
Web [www.tph-bausysteme.com](http://www.tph-bausysteme.com)

**TPH.**  
*Waterproofing Systems*