

Chemical breakdown, various substitutes for Custer Feldspar

	SiO ₂	Al ₂ O ₃	Fe ₂ O ₃	K ₂ O	Na ₂ O	TiO ₂	MgO	CaO		LOI
CUSTER	68.50%	17.00%	0.10%	10.00%	3.00%			0.30%		0.30%
MAHAVIR	67.10%	17.78%	0.07%	11.58%	2.70%	0.01%				0.32%
VARDHMAN	66.28%	17.98%	0.08%	11.25%	3.50%			0.50%		0.27%
G-200	65.90%	18.20%	0.09%	13.20%	1.52%		trace	0.75%		0.16%