

MAVERICK



REFINISHING PRODUCTS

301

Ultimate Gloss Clearcoat

PRODUCT

301

DESCRIPTION

ULTIMATE GLOSS CLEARCOAT

ACTIVATOR

30170

30180

30190

DESCRIPTION

FAST ACTIVATOR (LOW TEMP)

MEDIUM ACTIVATOR

SLOW ACTIVATOR (HIGH TEMP)

DESCRIPTION

301 is a general purpose clearcoat for automotive, truck and mobile equipment refinishing.

SURFACE PREPARATION

1. Allow final coat of basecoat to dry 15-30 minutes prior to applying clearcoat.
2. Use a tack cloth to remove any surface contaminants that may have settled on the basecoat.
3. Apply 401 Ultimate Gloss Clearcoat

MIXING RATIO (4:1)

301
4 Parts

30170, 30180, 30190
1 Part

APPLICATION

Apply 2-3 single flowing coats allowing a 10-15 minute flash between coats. Spray last coat to desired appearance.

Use 8-10 psi at the air cap when using HVLP, keeping 6-10 inches from substrate to avoid problems associated with air entrapment.

Note: Film thickness, flash times & temperatures may affect dry times.

DRY TIMES AT 77° F

1ST COAT FLASH TIME	2-5 MINUTES
2ND COAT FLASH TIME	4-9 MINUTES
3RD COAT FLASH TIME (OPTIONAL)	10-15 MINUTES
TO REMOVE FROM BOOTH	15-30 MINUTES
TO SAND & POLISH	2+ HOURS
TO DELIVER	2+ HOURS

MAVERICK



REFINISHING PRODUCTS

RECOATING

301 may be recoated after a 2+ hour air dry at 77°F.

BUFFING

Allow 2-6 hours air dry at 77°F before buffing. For dirt removal, lightly "nib sand" with 1500 grit wet sandpaper and polish with a micro type compound. Finish with a quality glazing compound.

POT LIFE

Pot life is 1-2 hours at 77°F

ACCELERATOR

Not recommended

FISHEYE ELIMINATOR

Not recommended

EQUIPMENT CLEAN-UP

Clean equipment immediately after use with a VOC compliant gun wash or high quality lacquer thinner depending on area regulations.

TECHNICAL DATA

Mixing Ratio:	4:1
Catalyst:	30170, 30180, 30190
Pot Life:	1-2 Hours
Dry Times:	2-6 Hours
Volume Solids (RTS):	24%
Film Build:	1.0-1.5 mils per full wet coat
Coverage:	393 sq. ft.
Disposal/Safety:	see SDS for this product
Humidity Resistance:	Excellent
Salt Spray Resistance:	Excellent
VOC (RTS)	4.4 lbs/gal

NOTE: MAVERICK Refinishing products are not recommended for use in temperatures below 60° F. Use below these temperatures will effect dry times and performance.

FOR INDUSTRY USE ONLY

Read SDS Before Use

The contents of the package must be blended with other components before the product can be used. Any mixture of components will have hazards of all components. Before opening the packages, read all warning labels. Follow all precautions.

The material is designed for application only by professionally trained personnel using proper equipment under controlled conditions, and is not intended for sale to the general public. SEE SDS AND PRODUCT LABELS FOR ADDITIONAL SAFETY INFORMATION.