



MAV 751B 2K Sealer (Black)

DESCRIPTION:

MAV 751B - 2K Sealer Black multi-purpose double pack 2K sealer, with strong filling power and fine adhesion, has excellent flexibility and impact resistance which can increase gloss and build of topcoat. Smooth paint film and non-sanding application.

COMPONENTS:

MAV 751B	2K Sealer	
MAV-7415	Fast Activator	<64°F
MAV-7416	Medium Activator	64-86°F
MAV-7417	Slow Activator	>86°F

SUBSTRATES:


Dried and sanded existing paint film, primers and putties.

SURFACE PREPARATION:



Remove wax, silicon or other contaminations with 3910 Degreaser.

MIX RATIO:




Temperature	Product	Weight	Volume
<64°F	MAV 751B	100	100
	MAV 7415	20	25
	MAV-1	20-30	20-30
64-86°F	MAV 751B	100	100
	MAV 7416	20	25
	MAV-2	20-30	20-30
>86°F	MAV 751B	100	100
	MAV 7417	20	25
	MAV-2/3	20-30	20-30

POT LIFE:



@ 77°F
30 minutes with MAV 7415
45 minutes with MAV 7416/ MAV 7417


APPLICATION:



Spray gun set up:

Gravity feed: 1.2-1.5mm
3-5kg/cm²
Siphon feed: 1.4-1.7mm
3-5kg/cm²

Please refer to gun manufacturer for proper spray pressure recommendations.



Coats & Thickness:
2-3 Coats, 40-60 um
Flash off time:5-10mins between coats @ 77°F

DRYING TIME:



@ 77°F
4~6 hours
@ 158°F
30 minutes

SANDING:

Non sanding: spray topcoat after surface drying
Drying sanding: P400-600
Wet sanding: P800-1000

Re-application

After surface drying or sanding, spray topcoats.



CLEARING:

Clean equipment immediately with solvent after application.

Note:

- Shelf Life: 2 years in original sealed can at cool and dry place at 41-95°F.

PHYSICAL DATA:

VOC: 4.7 lbs/gal

FOR PROFESSIONAL USE ONLY

Read MSDS Before Use

NOTE: The information in this data sheet is based on our knowledge and the current laws. It is always the responsibility of the user to fulfill the requirements of local rules and legislations. The uncertain factors may affect the application of products, such as the condition of substrate. We do not accept any liability on loss, damage and performance of products unless we issue a special agreement. Always read the latest Material Data Sheet and the Technical Data sheet before applying the products.