



# FRP Walkway Covers Technical Data sheet

## Key benefits

### Anti-Slip Top Surface

- FRP walkway covers have an anti-slip surface, that offer excellent slip resistance.

### Designed to enhance visual safety

- Through the choice of yellow colour, we can increase the important visual safety enormously.

### Quick

- FRP walkway covers can be installed by anyone, in all weather conditions, all year around.

### Versatile

- Our walkway covers are manufactured in FRP material that does not corrode. They can also be cut to size and customized to your exact measurements.



## Specification

Please specify this text to secure best practice and quality:

**Product:** FRP Walkway cover

**Colour:** Safety Yellow Ral 1003 (or any colour combination)

**Grit type:** Aluminium Oxide

**Grit size:** mesh 10 (offshore) mesh 20 (industrial)

**Slip resistance:** R13

## Slip resistance level

Real Safety's solutions are all classified with the highest scores as **R13**.

DIN 51130/Class	R9	R10	R11	R12	R13
Slip angle (°)	6-10	10-19	19-27	27-35	>35
Slip Resistance	Very Low	Low	Medium	High	Very High



# FRP Walkway Covers Technical Data Sheet

## Technical data

Smoke & Flame	ASTM E648 Nepa 253	Average Critical Radiant Flux: 1.04 Watts/cm <sup>2</sup>
	ASTM E662 NFPA 258	Average Maximum Density Corrected (Flaming): Average Specific Optical Density at 4.0 Minutes: 187
		Average Maximum Density Corrected (Non-Flaming): 341 Average Specific Optical Density at 4.0 Minutes: 311
	ASTM E84	Flame Spread: 20 Smoke Developed: 400 Flame Spread: 50 Smoke Developed: 90 (Vinyl)
	NFPA 258	Passed
Wear	Simulator: 30,000 cycles, 400 pounds	Little wear at end of test: Approximately 0.013 inch (0.33 mm) between worn and unworn sections of cover
Impact	Approx. 138 Joules (17 lb. pendulum), 60°F	Slip resistant coating detached at point of impact only No shattering occurred
Thermal Shock	Range: -40° to 150°F	After 20 cycles, visual inspection for cracking or melting revealed no sign of damage
Weathering	ASTM D4587	Lightness/Darkness (L*) - small change Redness/Greenness (a*) - small decrease Yellowness (b*) - slightly larger decrease

## Physical and chemical properties

Physical state and appearance	Solid
Colour	According to the product
Odour	According to the product
Boiling point	Undetermined
Melting point	> 400°C
Specific gravity	1.5 - 1.9 g/m <sup>3</sup>
Vapor density	Not applicable
Solubility	Not applicable
pH	Insoluble
Inflammation point	480°C
Autoignition temperature	Not auto-flammable
Decomposition temperature	Not applicable

## Grid Choice



**Offshore**  
For offshore and heavy industrial applications.



**Industry**  
For industrial and commercial applications.

For installation and cleaning guides, please contact us.

