



Step Nosing Technical Data Sheet

Key benefits

Enhance Safety

This product will enhance safety on existing stairs immediately.

Versatile

Our Step Nosing are manufactured in FRP, non-corrosive material. They can be retro-fitted onto stairs regardless of the surface base (steel checker plates, steel grating, concrete, wood etc.)

Quick

They can be installed by anyone, in all weather conditions all year round.



Specification

Please specify this text to secure best practice and quality:

Product: FRP Step Nosing


Color: Safety Yellow Ral 1003 (or any colour preference)

Grit type: Aluminium Oxide

Grit size: mesh 10 (offshore) mesh 20 (industrial)

Length: (see table or specify) **Width:** (see table or specify)

Slip resistance: R13



| Length (mm) | 450 | 600 | 750 | 900 | 1200 | 1500 | 1800 | 2100 | 2400 | 2700 | 3000 |
|----------------|-----|-----|-----|-----|------|------|------|------|------|------|------|
| Width (mm) | 75 | 75 | 75 | 75 | 75 | 75 | 75 | 75 | 75 | 75 | 75 |

Slip resistance level

Real Safety's solutions are all classified with the highest scores as R13.

| DIN 51130/Classe | R9 | R10 | RII | R12 | R13 | |
|------------------|----------|---------|---------|---------|-----------|--|
| Slip angle(°) | 6 -10 | 10 - 19 | 19 - 27 | 27 - 35 | > 35 | |
| Slip Resistance | Very Low | Low | Medium | High | Very High | |





Step Nosing Technical data sheet

Technical data

| | ASTM E648 Nepa 253 | Average Critical Radiant Flux: 1.04 Watts/cm2 | | | |
|---|---|---|--|--|--|
| | ASTM E662 | Average Maximum Density Corrected (Flaming): Average Specific Optical Density at 4.0 Minutes: 187 | | | |
| Smoke & Flame | NFPA 258 | Average Maximum Density Corrected (Non-Flaming): 341 Average Specific Optical Density at 4.0 Minutes: 311 | | | |
| | ASTM E84 | Flame Spread: 20 Smoke Developed: 400 Flame Spread: 50 Smoke Developed: 90 (Vinyl) | | | |
| | NFPA 258 | Passed | | | |
| Wear | Simulator: 30,000 cycles, 400 pounds | Little wear at end of test: Approximately 0.013 inch (0.33 mm) between worn and unworn sections of cover | | | |
| Impact Approx. 138 Joules (17 lb. pendulum), 60°F | | Slip resistant coating detached at point of impact only No shattering occurred | | | |
| Thermal Shock | Range: -40° to 150°F | After 20 cycles, visual inspection for cracking or melting revealed no sign of damage | | | |
| Weathering ASTM D4587 | | Lightness/Darkness (L*) - small change Redness/Greenness (a*) - small decrease Yellowness (b*) - slightly larger decrease | | | |

Physical and chemical properties

| Physical state and apprarance | Solid | | |
|-------------------------------|--------------------------|--|--|
| Colour | According to the product | | |
| Odour | According to the product | | |
| Boiling point | Undetermined | | |
| Melting point | > 400°C | | |
| Specific gravity | 1.5 - 1.9 g/m3 | | |
| Vapor density | Not applicable | | |
| Solubility | Not applicable | | |
| рН | Insoluble | | |
| Inflammation point | 480°C | | |
| Autoignition temperature | Not auto-flammable | | |
| Decomposition temperature | Not applicable | | |

Grid Choice



Offshore For offshore and

heavy industrial applications.



Industry

For industrial and commercial applications.

For installation and cleaning guides, please contact us.

