

Manufacturer's Specification Certification

SC3000 Double Net Straw-Coconut Blanket


Contents:	70% straw 30% coir fiber
Netting:	Double Polypropylene Photodegradable
Thread:	Photodegradable
Roll Size:	100.0 sq yards/ 83.6 sq meters*
Width:	8.00 feet/ 2.44 meters*
Functional Longevity:	18 – 24 months
Best Use:	1.5:1 slopes, Medium-flow, roadways
	* Standard sizes. Additional or custom sizes may be available.

SC3000 is a fully Photodegradable blanket. The netting is made from Double Polypropylene. The thread is Photodegradable, while the filament of matrix is 70% straw 30% coir fiber.

Blankets can be produced from 50 SY to 1,000 SY and be from 4 ft. to 16 ft. wide.

As described in Federal Highway Administration's Standard Specification FP-03 in Section 713.17 and as described by ECTC as a Type 3.B.



Test Method Description	MARV*
Mass/Unit Area ASTM D 6475	10.14 oz/sq yd
Tensile Strength –MD ASTM D 6818	100 lbs/ft*
Tensile Strength –TD ASTM D 6818	100 lbs/ft*
Thickness ASTM D 6525	0.25+ inches*
Light Penetration ASTM D 6567	10.6%
Water Absorption ASTM D 1117, ECTC TASC 00197	361%
Reported Fiber Length, 80 percent greater than	3 inches
Elongation –MD ASTM D 6818	29.7 lb/in
Elongation –TD ASTM D 6818	25.5 lb/in
Vegetated Shear Stress	10lb/ft ²
Vegetated Velocity	18ft/sec
Manning's "n" (0"-6")	0.035 *
Seedling Emergence	409%
C Factor	<0.25@1.5:1*
Permissible Shear Stress - ASTM D 7207	2.00 lbs/ft.*²*
Permissible rate of flow	8 ft/s*
*MARV-Expected Minimum Average Roll Value	
<p>Enviroscape ECM certifies that this product is designed to meet the above criteria and is manufactured to perform as described in the Federal Highway Administration's Standard Specification FP-03 in Section 713.17 and as described by ECTC as a Type 3.B.</p>	
 <hr/> Mark Deitering - Quality Manager	1/13/21 <hr/> Date