

www.strawblanket.com

Soil Saver Jute 500



Properties	Test Method	Typical Value
Yarn Fiber		Woven Jute undyed and unbleached
Yarn Count- Warp		78 per width minimum
Yarn Count- Weft		42 per linear Yard Minimum
Color		Natural (Brown, Earth Tone)
Fabric Width		48 in. or 1.22m
Fabric Length		225ft or 1.22m
Fabric Weight		.92lbs/sy or 500g/sm
Strands-Warp		19.5/ft or 64/m
Strands-Weft		14.0/ft or 46/m
Mass per Unit Area		14.7 oz/sy or 500g/sm
Wide Width Tensile-Dry (Warp/fill)	ASTM D-4595	300x175 lbs/ft 1.8x0.95 KN/M
Wide Width Tensile-Wet (warp/fill)	ASTM D-4595	125 x 65 lbs/ft 1.8x0.95 KN/M
Elongation at Break	ASTM D-4595	10x 10%
Open Area		60-65%
Durability		1-2yr
Water Velocity		8ft/sec or 2.4 m/sec
Unit Shear Test		.45lbs/sf
"C" Factor, 1.5:1 Slope		.005