

# ALLOY 20 TUBING



Alloy 20 is an austenitic, nickel-iron-chromium-molybdenum alloy with the addition of copper. This combination makes it preferable in applications involving sulfuric, phosphoric, and nitric acids. The chromium and molybdenum content provide good pitting and crevice corrosion resistance. This grade exhibits exceptional resistance to stress corrosion cracking (SCC) induced by chlorides. Alloy 20 can be utilized in a wide variety of chemical process environments and has good performance in most acids, alkalines, salts and seawater.

## PRODUCTION SPECIFICATIONS

ASME SB729, SB464, SB468/ASTM B729,  
B464, B468/NACE MR0175

## MECHANICAL PROPERTIES

Yield Strength 0.2% Offset	35 KSI min.
Tensile Strength	80 KSI min.
Elongation (min. 2in.)	30%

## DIMENSIONAL TOLERANCES

Outside Diameter (OD)	OD Tolerance	Wall Tolerance
1/4" Tubes	+/- .005"	+/- 15%
3/8" Tubes	+/- .005"	+/- 15%
1/2" Tubes	+/- .005"	+/- 15%

## SIZE RANGE

Outside Diameter (OD)	Wall Thickness
1/4" - 1/2"	.035" - .065"

Cold Finished and Bright Annealed Tube

## ALLOY 20 (UNS N08020) CHEMICAL COMPOSITION % (MAX.)

Cr	Chromium	19.0 - 21.0
Ni	Nickel	32.0 - 38.0
C	Carbon	0.07
Mo	Molybdenum	2 - 3%
Mn	Manganese	2.0
Si	Silicon	1.0
P	Phosphorus	0.045
S	Sulfur	0.035
Fe	Iron	31.0 - 44.0
Cu	Copper	3.0 - 4.0
Nb	Niobium	(8.0xC) 1 Max.

OD	Wall	ID	PSI
1/4" (.2500")	.035	.180	20,400
	.049	.152	30,000
3/8" (.3750")	.035	.305	13,200
	.049	.277	19,200
1/2" (.5000")	.049	.402	14,800
	.065	.370	20,400

All Pressure Ratings are approximate and for illustration purposes only.  
Values are not Guaranteed or Warranted.

## TYPICAL APPLICATIONS

Piping  
Heat Exchangers  
Steam Condensers  
Flue-Gas Desulfurization  
Food Processing  
Chemical Processing

## FABRICATION

The chemical composition of Alloy 20 allows excellent formability for bending and flaring, and the addition of Niobium provides minimal carbide precipitation during welding.

