

Installation, Care and Maintenance Manual Warranty Registration Document 11 NB THIS LEAFLET MUST BE LEFT WITH THE CONSUMER AFTER INSTALLATION;

All aspects of the installation of minerva are also covered in a DVD that is available to view on-line at www.minervaworksurfaces.co.uk

GUARANTEE AND IMPORTANT MAINTENANCE INFORMATION ENCLOSED.




About your minerva worktops

These worktops were developed to make solid surface an easy fit option without the need for specialist templating or tooling. By following these instructions we know that competent installers can achieve excellent results.

Preparation

The work surfaces and additional materials must be conditioned for at least 24 hours at room temperature prior to fitting.

 Work surfaces should be stored horizontal and flat in a dry, well-ventilated area.



Must not be stored vertical and on one edge

- The worksurfaces are supplied with a final matt finish and do not require any further surface finishing apart from areas that require joints and any cut ends or edges
- All surfaces should be checked for any damage and colour consistency prior to installation. If you are unsure of the colour consistency, sand a small patch of each of the adjoining boards to test this to ensure a satisfactory match before any installation is carried out. Ensure you are in a suitably lit environment, wipe the dust away and use a damp cloth to help get a true colour comparison.

Any claims after installation relating to inconsistency are not covered by the product warranty.


- Darker colours show scratches and marks more easily and should be treated with extra care and attention during and after installation.
- Dust particles will be generated during the cutting, routing, sanding and drilling of the worktops. As a result of this, it is important to ensure the area you are working in is well ventilated and an appropriate dust extraction system is used. Minerva solid surface is completely non-toxic, however the adhesive used for joints contains methyl methacrylate and ventilation should be considered to ensure fumes are dissipated.

Tooling required


2¹/₂ HP, 1850 watt router




 Mason mitre jig with 30mm guide ring and 12mm twin flute tungsten carbide tipped cutter.



Random orbital sander for finishing.



 Hot Melt Glue gun, glue, clamps or Seaming Tools



Also required:

Jointing kit - 1 kit per joint.


This kit is supplied with 2 part acrylic adhesive (10:1 adhesive and activator), 2 isopropyl alcohol wipes, 6 MDF Jointing Blocks and sandpapers in the following grades: P120, P240, P320, P500 grit and grey abrasive pad.



- We do not recommend the use of any finishing products to enhance the appearance of these worktops other than those supplied in the Care Kit. The surface is factory finished to a matt finish and we do not recommend that a higher gloss level is attempted.
- Only use the sanding grades recommended in this installation quide.

Planning your layout

- Angled joints must always be supported by either wall battens or cabinetry.
- No joints should be made above a dish washer, washing machine, washer dryer or in the area around cut-outs.
- Joints should be at least 100mm away from all cut-outs and dishwasher installations.




- Where a cabinet cannot offer full support, additional bracing must be added to the cabinet to ensure full support of the minerva joint at the front and the back. All joints should be supported across at least 3 points.
- Additional support may also be necessary where the cut out for a hob or sink requires the removal of part of the cabinet rail. In this situation the addition of a metal rail is recommended in order to prevent sagging or a potential weakness.



 When using minerva as part of a breakfast bar configuration, we advise that an overhang of up to 300mm is permitted, but



support is required every 600mm along the length.



- If any additional fixings are needed in the worksurface, you will need to drill a hole, and then use adhesive to secure a brass insert into the hole. You can then screw into the insert - Do not screw directly into the surface as this can cause the surface to split.
- Use of a Boiling Water tap is not recommended with acrylic bowls.
- Avoid pouring boiling water into empty acrylic bowls as this can lead to superficial crazing of the surface. Running cold water at the same time will help to prevent this.


Slow Cookers

 As all slow cookers may operate at varying temperatures, we would always advise use of a trivet, chopping board, heat mat etc. to protect the surface from any damage.

Freestanding cookers

- Ensure that the level of the hob does not sit below the worktop as this can cause direct transfer of heat or flame towards the acrylic surface.
- The edges of the appliance should not be in direct contact with the worksurface. In normal circumstances a gap is required around the

appliance to enable removal for service. This gap will allow sufficient clearance from the worksurface.




 If the installation incorporates an Aga or other heat storage range, we would recommend a minimum of 60mm clearance needs to be allowed from the edge of the cooker to the worksurface.

Hobs

 Ensure that any installed hob has adequate clearance from the surface, use the heat reflective tape supplied with the surface and the hob gasket where supplied, must be fitted. Direct heat contact can result in damage.


Cutting the worksurface

 Eye protection and a dust mask should be worn when cutting.



- Tops may be over-cut, with a saw, by a minimum of 5mm and trimmed back using a router with a 12mm cutter and the straight edge of a jig.
- Always ensure that both sets of the cut are adequately supported. When cutting from the underside of the material, use a soft pad to avoid scratching.

- If you are cutting using a hand held skill/ circular saw then cut face up. Cut edge should always be clean cut with the router.
- Please note that an expansion gap of 1mm per metre of worksurface is required when fitting the product between two walls.



Jointing the worksurface


- Use a router and 12mm cutter with a straight edge to cut the female worksurface to the desired length.
- To prepare the cut faces for jointing, each side of the joint needs to be square cut. The broken/profiled edge of the surface edge needs to be removed and a small matching radius sanded on the 'dog-leg' of the male side of the joint to ensure seamless effect is achieved.

To ensure the best fit of these faces, one should be cut face up and the other cut face down.


 Using the isopropyl alcohol wipe supplied in the jointing kit, clean the cut edges of the worksurface. Ensure all surfaces are clean, dry and free of debris and dirt including the surrounding areas before proceeding to the next stage



4. Position two layers of masking tape approx 3mm from the edge of each joint line.




- 5. It is essential that the joint is dry fitted before bonding, to check it has been machined correctly. The joint surfaces may require block sanding to ensure the cut edge is true. This will ensure that the two machined edges will draw together flush.
- 6. If not using the Optional Joint pulling tools then using the Hot Melt adhesive bond and position the 6 blocks (3 each side of the joint) just outside the masked area and lined up so a clamp can be positioned at either side to pull the joint together.



 Ensure that the appropriate adhesive colour cartridge for the worksurface décor is being used.


It is recommended that disposable gloves are worn when handling the adhesive.




Mix the adhesive as per the instructions with the pack



- 8. Position the first worksurface onto the base units and apply a coating of the 2-part acrylic adhesive onto the cut edge of the first board.
- Apply adhesive to the cut edge of the second board.




- 10. Using either the Seaming Tool or clamps on the glued blocks pull worksurfaces together leaving a gap of approximately 5mm and apply a further bead of adhesive along the gap and into the front edge of the joint.
- 11. Ensure the surfaces are level and tighten together.





NB. The working time of the adhesive once mixed is around 8-10 minutes depending on ambient temperature.


12. Before the adhesive starts to cure, bridge the strips of masking tape lightly with a spatula or scraper and remove any excess adhesive.



- 13. Ensure masking tape is removed before adhesive cures leaving a small bead line.
 - The hardening time of the adhesive depends on the ambient temperature and the amount of adhesive applied.
 - The hardening can be checked with a fingernail or by checking the adhesive in the sachet.
 - Tapping the MDF blocks with a sideways motion will normally remove them quite easily. If not, lever them off or carefully use a sharp chisel to break the bond with the surface.
- 14. Once cured, the bead of adhesive can be removed by sanding with a random orbital sander with the following order of sandpaper grades: P120 to remove the adhesive bead, P240, P320, P500 grit and then finish with grey abrasive pad and a light mist of water. All stages must be carried out with the random orbital sander.



- Ensure that dust is removed between sanding processes.
- Sand across, up and down then across, up and down in a north - south, east – west style.



 When changing the sandpaper grade, increase the sanding area slightly to blend in.

Hob and Sink cutting

 Making a cut-out in the worksurface for inset hobs, sinks and Belfast sinks it is important to follow the instructions in this section very carefully, especially when making hob cut-outs.

Failure to do so may invalidate the product warranty.

When a matching solid surface splashback is being fitted behind a hob area a minimum of 30mm clearance should be allowed from edge of the hob to the splashback face.

TOP TIP 1

WHEN CUTTING A HOB OR SINK CUT OUT
WE WOULD RECOMMEND THAT THE
MINERVA WORKSURFACE IS PLACED ON
A SOLID SUBSTRATE WHILST MACHINING.


THIS WILL ENSURE THE CUT OUT DOES NOT DROP AND CAUSE EITHER INJURY OR DAMAGE TO THE SURFACE.

TOP TIP 2

IF MAKING A CUTOUT IT CAN SOMETIMES BE BENEFICIAL TO FABRICATE YOUR OWN JIG FROM MDF

- Mark the cut out in line with the instructions or template supplied with the sink or hob being used
- 2. Mill the cut-out using a router and cutter with minimum 20mm diameter.

- The internal corner radii of the cut-out must be at least 10mm, and the spacing between the hob unit and the worktop must be at least 7mm to allow for air to circulate
- A radius of at least 3mm must be milled or sanded to the top edge of the solid surface material.
- 3. Metal clamping clips should be provided to clamp the sink down onto the worksurface.
- 4. Use a silicone sealant to bed the sink onto the worksurface.
- HOBS Please note that heat resistant tape must be applied around the entire hob cut-out with a slight overlap on the work surface underneath as illustrated below.



- 6. The foam strip or gasket provided by the hob supplier must always be fixed under the rim prior to installation of the hob.
- Please note that dishwashers, washing machines and driers should have a diffuser plate mounted to the underside of the worksurface or heat reflective tape.
- 8. Make a hole for taps using standard tooling cutting from the top surface.
- 9. Soften the edge of the cut out with a P320 paper to eliminate any sharp edges.



10. Apply the supplied heat reflective tape to the inside of the cut overlapping by approximately 4mm on the top surface.

Belfast sink cut outs

Belfast sink cut outs should be cut and finished in the same manner.

Take particular care when handling the cut worktop as the resultant cut out leaves a potential weak point to the back edge.

Drainer grooves can be cut to the required length, depth and configuration using a proprietary jig. These jigs usually include the slope to facilitate correct drainage.

Fitting a 'boiling water' tap

 Use a router and 12mm twin flute cutter to machine a hole in accordance with the tap It may be necessary to use additional brackets to support the end panel or to fix it to the floor or cabinet.

Edge finishing

- 1. Cut the worksurface to length +5mm using a saw.
- 2. Trim to exact size using a router to ensure the edge is clean and straight.
- 3. Using a Random Orbital sander gently soften the top edge and surface with the P240, then using the P320 followed by the P500 grit and finally with the grey abrasive pad and a light mist of water to blend.

Cutting curves

minerva worktops can easily be cut to form curves or shapes.

We recommend using a jig which should allow you to form clean edges to your required radius.

Always remember the jig needs to allow for the size of your router base.

Cut edges are simply sanded using the 3 grades of sandpaper and the grey finishing pad

Fitting an alternative sink

 If you are using an alternative sink to the offering in the minerva range, please refer to the manufacturers guide or the section relating to this on our website.

Fitting undermount sink module

When planning for utilising a sink module, care should be taken to ensure that any jointing to be completed is not positioned within 100mm from the sink area and that enough additional worksurface is available to complete any required joint into the module.

List of components

- Sink bowls are supplied separate from the module so ensure that the correct number of additional cartons are available. e.g The 1 & 1/2 bowl module is supplied in 3 boxes - sink module, large bowl and small bowl.
- Some modules include a pop-up waste kit. Waste fittings and silicone sealant come with all modules.
- 1. Unpack module ensuring that all required components are present and correct.
- 2. Ensure there are no marks or issues with the worksurface and sinks before commencing any work.

- It is important not to stand or kneel on the sink module area.
- 4. Dry fit/position the module in the area/cabinet it is to be fitted. Make sure you have adequate supply of standard worksurface for extension to the module.
- Ensure you position the module with the bowls and drainer positioned according to your requirements.
- Before fitting the bowl(s) and fittings into position it is recommended that all joints and edgings be machined as described previously in the booklet.
- 7. Once you are confident all the joints and edgings have been machined as required.

Dry fit joints to check

- 8. Unpack stainless steel bowl(s) and fittings ensuring all components are present and not damaged.
- Clean the surfaces on the bowl edges to be mounted and the edge of the module where the sink will be bonded, ensuring that all dust, debris and dirt is removed.
- 10. Apply a generous bead of the supplied silicone to the stainless steel bowl edge area and apply to the worksurface ensuring no gaps are left anywhere in the bead to achieve a watertight fit.
- 11. Apply each sink carefully making sure to check the waste overflow is positioned correctly and insert screw fixings and sink clips to the underside, carefully applying and ensuring the screw is not over-tightened as this can result in damage to the material.

DO NOT USE A POWER DRIVER. USE A HAND TOOL

- 12. Check sink positions are even and correct and adjust if necessary.
- 13. Position the module in the unit and make necessary joints into the module as required using the aforementioned processes.
- 14. Wipe away any excess silicone.
- 15. Allow 24 hours for the silicone to fully cure before using the sink (i.e. filling with water).

Handy Tips

 When tiling down to the worksurface leave a minimum of 3mm gap between the bottom row of tiles and the worksurface. This gap should be sealed with a silicone sealant.

Do not fill the gap with grout.

- When scribing the worktop to the back wall use an electric planer with TCT blades.
- When fitting sink modules it is a good idea to dry fit onto the cabinet in order to mark out the positioning of the bowl to the front & back rails of the carcass. This will enable the easy removal of excess rail to allow for correct sink positioning.

Before installation please thoroughly check your surfaces for damage and colour consistency

Surface finish

Over a short period of time in use in the home, your worktops will develop a smoother finish and more lustrous appearance. In the first days

after installation the dry finish of the surface may show finger marks more readily than it will do when it has achieved this 'patina'. Regular cleaning with warm soapy water is the usual first step to remove surface marks.

If grease marks remain, the gentle abrasive of Cif cream cleaner will remove most marks without harming the surface at all. This sort of cleaner has a positive effect on the acrylic surface. For very stubborn grease marks or burnt on areas of fat splashes for instance, Fairy Power Spray will cut through this very easily.

It is possible to enhance the surface lustre by using Countertop cleaner; as with any treatment of this nature, the application has to be repeated in order to maintain the same finish across all areas of the kitchen.

Initial treatment and cleaning

First ensure that your worksurface is thoroughly cleaned with warm soapy water or Fairy Power Spray to remove any greasy residues. A mild abrasive cream cleaner such as Cif cream is also a good part of your regular maintenance regime.

Countertop cleaner

Countertop cleaner is designed to give lustre to solid surface worktops – this will be particularly noticeable on darker décors. It will also help to build up the natural patina of your surface and a protective layer that will repel dirt and liquids. We advise to use sparingly, as required. Apply the cleaner using a micro-fibre cloth* and buff to leave a streak free finish. Countertop cleaner will not remove scuffs or scratches but can mask the effect.

WHENEVER TRYING TO REMOVE MARKS OR SCRATCHES ALWAYS TRY THE LEAST SEVERE METHOD FIRST

- Everyday marks Using a mild abrasive cleaner such as Cif cream, work in a circular motion; wipe away all residue and buff dry. Apply Countertop cleaner if applicable.
- 2. Fine scuffs and scratches Cover the affected area with a liberal amount of soapy water. Place the grey abrasive pad* onto the wet surface and, using a sanding block* or firm sponge to ensure even spread of pressure, rub over the affected area in a circular motion. A slight paste will be generated that aids the finishing process and helps to maintain the original level of surface finish. Repeat step 1. If marks are still evident, repeat the grey abrasive pad process or, in the case of deeper scratches, move on to step 3.
- Removal of deeper scratches Ensure that the surface is clean and dry before starting. Place the sanding disc* onto the sanding block ensuring that it is located correctly and wrapped onto both sides of the block.

Using small circular movements, work a small area around the affected part of the surface. A small amount of dust will be generated – this will need to be wiped off to check progress and before moving onto the next step. When the mark has been removed the repaired area will retain very fine sanding marks; these are removed by repeating step 2 and then step 1 to blend in the refurbished area. Each time you move back through the steps, work a slightly wider area so as to help this blend in.

Items marked with '*' are included as part of the Care Kit available from your retailer.

Please Note

Darker colours show scratches and marks more easily and should be treated with extra care and attention during and after installation.

Cleaning with a sponge, water and mild detergent liquid is sufficient for normal

Cleaning your worksurface

THINGS TO DO THINGS TO AVOID To prevent damage from hot objects, **Do not** place hot objects directly on the always use heat resistant mats or trivets worktop. e.g. pans, steamers. on the surface of the worktop. Always use a chopping board for **Do not** cut directly on the worktop. preparing food. Heavy crockery, kitchen utensils and other objects sliding on a worksurface can produce fine scratches. Wipe spilt liquids away. Ensure that all **Avoid** contact with aggressive chemical inset appliances are properly sealed as substances such as nail polish remover, per fitting instructions. chlorine, acetone, drain cleaner etc. Wipe immediately with damp cloth. **Do not** use very abrasive cleaners and Dried on residues can be removed with solvents as cleaning agents. a mild abrasive domestic cleaner. Rub gently, rinse and wipe dry.

Mark and stain removal

maintenance.

FOODS: Tea, coffee, milk, fruit juice, curry, red wine, vinegar, lemon juice and beetroot can all be removed using a damp cloth, warm water and a mild detergent.

GENERAL HOUSEHOLD			
Stain/Mark	Damp cloth	Warm water and mild detergent	White spirit
Oil	•	•	
Water based paint		•	
Solvent based paint		•	•
Permanent Dyes			•
Shoe polish			•
Biro		•	
Lipstick		•	

WARRANTY

Your worktops have a 10 year warranty against manufacturing defects. In the unlikely event of there being any problems with this product, please refer in the first instance back to your retailer.

It is imperative that the installation and care and maintenance instructions are referred to both before and after installation, as misuse of the worksurface may affect the appearance of the product. This does not affect your statutory rights as a consumer.

Complete the form on page 14 or register online at www.minervawarranty.co.uk

The warranty applies to the first owner and first installation only and is not transferable.

07/18

WARPANTY DECISTRATION FORM: minerva

Name
Address
Post Code
Tel
Email
Where did you purchase the work surface?
Product reference number
Date of purchase
Product reference number can be found on the minerva packaging and on the underneath of the work surface.
To be completed by installer I certify that this <i>minerva</i> work surface has been fitted in accordance with the prescribed installation instructions.
Signed
Date
Please print name

Please return to: Sylmar Technology Ltd, Azalea Close, Clover Nook Industrial Park, Alfreton, Derbyshire DE55 4QX Tel: 01773 521300 Fax: 01773 836837 E-mail: sales@sylmar.co.uk

Or register warranty online at ${\bf www.minervawarranty.co.uk}$

Data Protection: Sylmar Technology Limited may use your information for administration, customer analysis, customer service and targeted marketing. We may contact you by email, SMS, telephone, fax or other reasonable methods to let you know about other products, services or promotions that may be of interest to you. If you do not want to receive such information and offers then please tick \Box





Scan QR code to view our on-line video instruction.



