

# Product: WRE

## Description

Hunt Process All Resin White Pigmented was developed in order that efficient and economical curing could be obtained simultaneously with a reduction in the maximum temperatures within a concrete slab due to absorption of infra-red. Such control of the temperature is desirable during the early life of the concrete in order to reduce the expansion and contraction stresses resulting from extreme temperature changes. The film resulting from Hunt Process All Resin White Pigmented weathers away gradually by chalking and not by peeling. Hunt Process All Resin Water Base Concrete Curing Compound is a non-hazardous material.

## Specifications:

Hunt Process All Resin Water Base Concrete Curing Compound (WRE) will meet the following specifications:

ASTM C-309, Type II, Class: "B"  
AASHTO M-148, Type II, Class:"B"

Test Results:	C-309
	ASTM
Moisture retention -	.50
Reflectance -	62%
Dry Time -	<4 hrs.

## Application: Rate, Time, and Method

Hunt Process All Resin White Pigmented should be applied at a rate of 200 square feet per gallon to a fresh concrete surface by spraying immediately following the finishing operation and disappearance of the surface water sheen. Simple pressure spray equipment, either hand or power operated, with a fan type nozzle is recommended for uniform and efficient coverage.

## Agitation:

Slight or no agitation is required. Do not over mix. Do not dilute with any other compound. **Water Base Concrete Curing Compound should be protected from freezing.**

## MANUFACTURER HUNT PROCESS CORP.-SOUTHERN

TELEPHONE  
601-856-8811

*"Spray it and Forget it"*

POST OFFICE 688  
Ridgeland, MS 39158

We guarantee our product to Hunt Process quality control. NO OTHER WARRANTY OR GUARANTEE, EXPRESSED OR IMPLIED, INCLUDING BUT NOT LIMITED TO, THOSE CONCERNING MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, IS MADE BY HUNT PROCESS CORP.-SOUTHERN. We assume no responsibility for coverage, performance or injuries resulting from use. Liability, if any, is limited to replacement of products. In no event will Seller be liable for any loss of profits or other special or consequential damages, even if Seller has been advised of the possibility of such damages.