



www.oldwesternpaint.com

OLD WESTERN PAINT CO., INC.
2001 W. Barberry Place, Denver, CO 80204
303-825-5147
Toll Free 1-888-765-9827

paint@oldwesternpaint.com

PRODUCT INFORMATION
LV1200 POLY FAUX CONJUGATED OIL VARNISH
Polyurethane Faux Coating

Mahogany Sensation, Natural Walnut, Caramel Coffee, Royal Brown, Imperial Gold, Silky Chocolate, Silhouette Black, Modern Gray

TYPE: One packaged oil modified
100% pure polyurethane.

DESCRIPTION: POLY FAUX

Polyurethane is a unique, durable interior coating system designed to help create a rich faux stain look. For use on wood and concrete floors. **POLY FAUX** can brighten up any old worn wood or concrete floor. Perfect for staining or discolored wood or concrete floors. Brings new life to any room with many color choices to meet your specific needs. Easy to maintain. To change color, simply recoat, giving a new faux or stain look. Can have an uneven edge look as Poly Faux is a decorative and unique coating.

CLEAN UP: Mineral Spirits or Paint Thinner

APPLICATION:

Brush, Flat Pad Applicator, Wool Pad.
Surface should be free from dust, dirt, wax, peeling paint or any loose substance. Surface must be screened and completely dry.
First coat: Apply a generous coat by swirling applicator to achieve a faux look, or pull straight for an even look, maintaining a wet edge throughout the coating job. Let dry completely, approximately 8-12 hours.
Second coat: After 12 hours or when dry, and before 48 hour hard dry, apply using first coat method.
If dry time of first coat exceeds 48 hours, screen, for good adhesion, tack, then apply second coat. The use of a different color on the second coat will help achieve a contrasting faux design. Two coats recommended. Can topcoat with *Poly Var Clear Polyurethane* in desired sheen.
Do not apply over stearated sanding sealers. Not recommended for garage floors, not suited for hot tire pick-up.

SPREADING RATE:

First coat: 350 – 400 square feet per gallon.
Second coat: 400 – 450 square feet per gallon.
Spreading rate subject to surface porosity, texture and application method.

DRYING TIME:

Dries in 2-4 hours (dust-free), recoat 12 hours or when completely dry. Drying time may be affected by excessive humidity, low temperature, failure of air movement and thickness of finish.

ANALYSIS:

SOLIDS BY WEIGHT	49.00%
SOLIDS BY VOLUME	41.00%
SOLVENT TYPE	Aliphatic

GLOSS 60 Degree:

1200PFG Gloss	95-97
1200PFV Velvet	34-40
1200PFS Satin	28-34

MAINTENANCE:

Allow coating to cure completely. Always clean well with *Poly Glow Hardwood Floor Maintainer*. *Poly Glow* leaves no residue and assures a clean, beautiful sheen that alleviates complications if future coating is desired. *Poly Glow* is 100% biodegradable and pH-neutral, safe to use on almost any hard surface.

Available in: Satin, Velvet, Gloss sheens