

## **Duo Patch**

### Two component polymer-modified concrete repair mortar

A two-component, polymer modified concrete repair mortar with integral corrosion inhibitor for use in horizontal, form and pour and when mixed to a stiffer consistency, vertical and overhead applications.

#### **BENEFITS**

- Contains integral corrosion inhibitor
- Suitable for repairs from featheredge to 2"
- Interior/exterior overlayment applications
- Excellent durability and adhesion
- Excellent freeze-thaw durability
- Easy to trowel, high slump consistency
- Dries to natural concrete gray color

#### **USAGE**

- Industrial warehouse
- Parking deck
- Roadway applications subjected to heavy loads and abrasion
- Decorative overlays
- Resufacing worn concrete walkways
- Horizontal and vertical repairs

#### **PACKAGING**

- 50 lb bag of Duo Patch + 1 gal. jug of **Duo Patch Admix**
- 60 lb pail unit containing 50 lb bag of Duo Patch + 1 gal. jug of Duo Patch Admix









# **Duo Patch**

## Two component polymer-modified concrete repair mortar



### **TYPICAL TEST DATA**

Set Time at 70°F (ASTM C-266)	
Initial Set	40 min
Final Set	50 min
Compressive Strength (ASTM C-109)	
1 Day	2500 psi
7 Days	4000 psi
28 Days	6000 psi
Bond Strength (ASTM C-882)	
7 Days	1800 psi
Length Change (ASTM C-157)	
Wet Cure @ 28 Days	+.04%
Air Cure @ 28 Days	02%
Flexural Strength (ASTM C-348)	
7 Days	650 psi
28 Days	1300 psi
Yield	
Yield per bag	.42 cu-ft



